

## SABIC Innovative Plastics XYLEX X8409AC PC+POLYESTER (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/PET Polyester Blend , Polyester, TP , Polyethylene Terephthalate (PET)

### Material Notes:

PC + Polyester, Injection (Blow) Molding, or Extrusion Blow molding grade, Chemical Resistance and Transparency

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-XYLEX-X8409AC-PCPOLYESTER-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-XYLEX-X8409AC-PCPOLYESTER-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.130 %	0.130 %	23 <sup>o</sup> C / 50% RH; ISO 62
Water Absorption at Saturation	0.37 %	0.37 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0080 cm/cm @Thickness 3.20 mm	0.0050 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Linear Mold Shrinkage, Transverse	0.0050 - 0.0080 cm/cm @Thickness 3.20 mm	0.0050 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	4.0 g/10 min @Load 2.16 kg, Temperature 265 <sup>o</sup> C	4.0 g/10 min @Load 4.76 lb, Temperature 509 <sup>o</sup> F	ASTM D1238
Melt Index of Compound	3.0 g/10 min @Load 2.16 kg, Temperature 265 <sup>o</sup> C	3.0 g/10 min @Load 4.76 lb, Temperature 509 <sup>o</sup> F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	Type I, 50 mm/min; ASTM D638
	60.0 MPa	8700 psi	50 mm/min; ISO 527
Tensile Strength, Yield	57.0 MPa	8270 psi	Type I, 50 mm/min; ASTM D638
	60.0 MPa	8700 psi	50 mm/min; ISO 527
Elongation at Break	92 %	92 %	Type I, 50 mm/min; ASTM D638
	117 %	117 %	50 mm/min; ISO 527
Elongation at Yield	5.8 %	5.8 %	50 mm/min; ISO 527
	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638

Tensile Modulus Mechanical Properties	2.18 GPa Metric	316 ksi English	1 mm/min; ISO 527 Comments
	2.37 GPa	344 ksi	50 mm/min; ASTM D638
Flexural Strength	89.0 MPa	12900 psi	2 mm/min; ISO 178
Flexural Yield Strength	94.0 MPa	13600 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	2 mm/min; ISO 178
	2.22 GPa	322 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	8.54 J/cm	16.0 ft-lb/in	ASTM D256
	2.00 J/cm	3.75 ft-lb/in	ASTM D256
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Izod Impact, Notched (ISO)	10.0 kJ/mÂ²	4.76 ft-lb/inÂ²	80*10*4; ISO 180/1A
	8.00 kJ/mÂ²	3.81 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -10.0 Â°C	@Temperature 14.0 Â°F	
	8.00 kJ/mÂ²	3.81 ft-lb/inÂ²	80*10*4; ISO 180/1A
	@Temperature -30.0 Â°C	@Temperature -22.0 Â°F	
Charpy Impact, Notched	0.800 J/cmÂ²	3.81 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	70.0 J	51.6 ft-lb	ASTM D3763
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	60.0 Âµm/m-Â°C	33.3 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
	104 Âµm/m-Â°C	57.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	104 Âµm/m-Â°C	57.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
CTE, linear, Transverse to Flow	70.0 Âµm/m-Â°C	38.9 Âµin/in-Â°F	ISO 11359-2

Thermal Properties	Metric @Temperature 23.0 - 30.0 Â°C	English @Temperature 73.4 - 144 Â°F	Comments
	104 Âµm/m-Â°C	57.8 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	104 Âµm/m-Â°C	57.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
Thermal Conductivity	0.230 W/m-K	1.60 BTU-in/hr-ftÂ²- Â°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	116 Â°C	241 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	102 Â°C	216 Â°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	104 Â°C	219 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	121 Â°C	250 Â°F	Rate B/50; ISO 306
	123 Â°C	253 Â°F	Rate B/120; ISO 306
	123 Â°C	253 Â°F	Rate B/50; ASTM D1525

Optical Properties	Metric	English	Comments
Refractive Index	1.576	1.576	ASTM D542
Haze	1.5 %	1.5 %	ASTM D1003
	@Thickness 2.54 mm	@Thickness 0.100 in	
Transmission, Visible	88 %	88 %	2.54 mm; ASTM D1003

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China