

SABIC Innovative Plastics XYLEX X8419 PC+POLYESTER (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/PET Polyester Blend , Polyester, TP , Polyethylene Terephthalate (PET)

Material Notes:

Low-medium flow, suitable for blow molding, injection molding, extrusion.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-XYLEX-X8419-PCPOLYESTER-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
Moisture Absorption	0.0500 %	0.0500 %	23 ^o C / 50% RH; ISO 62
Water Absorption at Saturation	0.12 %	0.12 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0080 cm/cm @Thickness 3.20 mm	0.0050 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	6.0 g/10 min @Load 2.16 kg, Temperature 265 ^o C	6.0 g/10 min @Load 4.76 lb, Temperature 509 ^o F	ASTM D1238
Melt Index of Compound	6.0 g/10 min @Load 2.16 kg, Temperature 265 ^o C	6.0 g/10 min @Load 4.76 lb, Temperature 509 ^o F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	55.0 MPa	7980 psi	Type I, 50 mm/min; ASTM D638
	110 MPa	16000 psi	50 mm/min; ISO 527
Tensile Strength, Yield	55.0 MPa	7980 psi	Type I, 50 mm/min; ASTM D638
	60.0 MPa	8700 psi	50 mm/min; ISO 527
Elongation at Break	120 %	120 %	50 mm/min; ISO 527
	130 %	130 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	5.8 %	5.8 %	50 mm/min; ISO 527
	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	1.90 GPa	276 ksi	1 mm/min; ISO 527

Mechanical Properties	2.10 GPa Metric	305 ksi English	5 mm/min: ASTM D638 Comments
Flexural Yield Strength	80.0 MPa	11600 psi	2 mm/min; ISO 178
	85.0 MPa	12300 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	1.3 mm/min, 50 mm span; ASTM D790
	2.05 GPa	297 ksi	2 mm/min; ISO 178
Izod Impact, Notched	7.50 J/cm	14.1 ft-lb/in	ASTM D256
	0.700 J/cm @Temperature -30.0 Â°C	1.31 ft-lb/in @Temperature -22.0 Â°F	ASTM D256
Izod Impact, Notched (ISO)	11.0 kJ/mÂ²	5.23 ft-lb/inÂ²	80*10*4; ISO 180/1A
	7.00 kJ/mÂ² @Temperature -30.0 Â°C	3.33 ft-lb/inÂ² @Temperature -22.0 Â°F	80*10*4; ISO 180/1A
Charpy Impact, Notched	1.80 J/cmÂ²	8.57 ft-lb/inÂ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	68.0 J	50.2 ft-lb	ASTM D3763
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	69.0 Âµm/m-Â°C	38.3 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	71.0 Âµm/m-Â°C	39.4 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
CTE, linear, Transverse to Flow	69.0 Âµm/m-Â°C	38.3 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	71.0 Âµm/m-Â°C	39.4 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	98.0 Â°C	208 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	98.0 Â°C	208 Â°F	

Thermal Properties	@Thickness 3.20 mm Metric	@Thickness 0.126 in English	Comments
Vicat Softening Point	115 Å°C	239 Å°F	Rate B/50; ASTM D1525
	115 Å°C	239 Å°F	Rate B/50; ISO 306
	115 Å°C	239 Å°F	Rate B/120; ISO 306

Optical Properties	Metric	English	Comments
Haze	<= 2.0 % @Thickness 2.54 mm	<= 2.0 % @Thickness 0.100 in	ASTM D1003
Transmission, Visible	89 %	89 %	2.54 mm; ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China