

SABIC Innovative Plastics Xenoy[®] X5300WX PBT+PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Unreinforced, opaque PBT+PC alloy. Chemical resistance and good mechanical performance. UV-stabilized. Excellent weatherability.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Xenoy-X5300WX-PBTPC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D792
Density	1.23 g/cc	0.0444 lb/in ³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23 [°] C / 50% RH; ISO 62
Water Absorption at Saturation	0.50 %	0.50 %	ISO 62
Linear Mold Shrinkage, Flow	0.0070 - 0.0090 cm/cm @Thickness 3.20 mm	0.0070 - 0.0090 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	26 g/10 min @Load 5.00 kg, Temperature 266 [°] C	26 g/10 min @Load 11.0 lb, Temperature 511 [°] F	ASTM D1238
Melt Index of Compound	25 g/10 min @Load 5.00 kg, Temperature 265 [°] C	25 g/10 min @Load 11.0 lb, Temperature 509 [°] F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	51.0 MPa	7400 psi	Type I, 50 mm/min; ASTM D638
	51.0 MPa	7400 psi	50 mm/min; ISO 527
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
	62.0 MPa	8990 psi	50 mm/min; ISO 527
Elongation at Break	110 %	110 %	Type I, 50 mm/min; ASTM D638
	110 %	110 %	50 mm/min; ISO 527
Elongation at Yield	5.0 %	5.0 %	Type I, 50 mm/min; ASTM D638
	5.0 %	5.0 %	50 mm/min; ISO 527
Tensile Modulus	2.25 GPa	326 ksi	1 mm/min; ISO 527
	2.55 GPa	370 ksi	50 mm/min; ASTM D638

Mechanical Properties	Metric	English	Comments
Flexural Yield Strength	97.0 MPa	13900 psi	2 mm/min; ISO 178
	96.0 MPa	13900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.18 GPa	316 ksi	2 mm/min; ISO 178
	2.48 GPa	360 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.47 J/cm	14.0 ft-lb/in	ASTM D256
	1.80 J/cm	3.37 ft-lb/in	ASTM D256
	@Temperature -30.0 Å°C	@Temperature -22.0 Å°F	ASTM D256
Izod Impact, Notched (ISO)	50.0 kJ/mÅ²	23.8 ft-lb/inÅ²	80*10*4; ISO 180/1A
	15.0 kJ/mÅ²	7.14 ft-lb/inÅ²	80*10*4; ISO 180/1A
	@Temperature -30.0 Å°C	@Temperature -22.0 Å°F	80*10*4; ISO 180/1A
Charpy Impact, Notched	4.50 J/cmÅ²	21.4 ft-lb/inÅ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	71.0 J	52.4 ft-lb	ASTM D3763
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 Åµm/m-Å°C	38.9 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	70.2 Åµm/m-Å°C	39.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	75.0 Åµm/m-Å°C	41.7 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
	75.6 Åµm/m-Å°C	42.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	101 Å°C	214 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	89.0 Å°C	192 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Thermal Properties	Metric	English	Comments
	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
	88.0 Å°C	190 Å°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	120 Å°C	248 Å°F	Rate B/50; ISO 306
	124 Å°C	255 Å°F	Rate B/120; ISO 306
	135 Å°C	275 Å°F	Rate B/50; ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China