

## SABIC Innovative Plastics Xenoy® X5630P PET+PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/PET Polyester Blend , Polyester, TP , Polyethylene Terephthalate (PET)

### Material Notes:

Mineral filled PC/PET blend with high heat dimensional stability, low shrinkage and low CTE, especially for painted applications

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-Xenoy-X5630P-PETPC-Europe-Africa-Middle-East.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Xenoy-X5630P-PETPC-Europe-Africa-Middle-East.php)

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption	0.140 %	0.140 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.42 %	0.42 %	ISO 62
Melt Index of Compound	15 g/10 min @Load 5.00 kg, Temperature 265 °C	15 g/10 min @Load 11.0 lb, Temperature 509 °F	MVR [cm <sup>3</sup> /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 MPa	7250 psi	5 mm/min; ISO 527
Tensile Strength, Yield	56.0 MPa	8120 psi	5 mm/min; ISO 527
Elongation at Break	8.0 %	8.0 %	5 mm/min; ISO 527
Elongation at Yield	3.2 %	3.2 %	5 mm/min; ISO 527
Tensile Modulus	4.15 GPa	602 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	4.05 GPa	587 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	8.00 kJ/m <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
	6.00 kJ/m <sup>2</sup> @Temperature -30.0 °C	2.86 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	100 kJ/m <sup>2</sup>	47.6 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U
	80.0 kJ/m <sup>2</sup> @Temperature -30.0 °C	38.1 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	80*10*4; ISO 180/1U
Charpy Impact, Notched	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	Edgew 80*10*4 sp=62mm; ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	52.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	28.9 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-2
	@Temperature -30.0 - 80.0 $^\circ\text{C}$	@Temperature -22.0 - 176 $^\circ\text{F}$	
CTE, linear, Transverse to Flow	72.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	40.0 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	ISO 11359-2
	@Temperature -30.0 - 80.0 $^\circ\text{C}$	@Temperature -22.0 - 176 $^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	110 $^\circ\text{C}$	230 $^\circ\text{F}$	Flatw 80*10*4 sp=64mm; ISO 75/Af
Vicat Softening Point	137 $^\circ\text{C}$	279 $^\circ\text{F}$	Rate B/50; ISO 306
	140 $^\circ\text{C}$	284 $^\circ\text{F}$	Rate B/120; ISO 306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China