

## SABIC P5510 Black High Density Polyethylene for Pipes

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Pipe Grade

### Material Notes:

**Product Description:** P5510 is a black compound high density (class MRS 8 - PE 80) polyethylene with bimodal distribution of molecular mass. It is specifically designed for Pressure Pipe applications. It provides excellent stress crack resistance properties combined with very good long term hydrostatic strength. **Typical Applications:** Pressure pipes for drinking water, irrigation, gas distribution and waste water pipes. It is also recommended for the manufacture of chemical liners and containers. Information provided by SABIC.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-P5510-Black-High-Density-Polyethylene-for-Pipes.php](http://www.lookpolymers.com/polymer_SABIC-P5510-Black-High-Density-Polyethylene-for-Pipes.php)

Physical Properties	Metric	English	Comments
Density	0.956 g/cc	0.0345 lb/in <sup>3</sup>	ISO 1183
Oxidative Induction Time (OIT)	>= 20 min @Temperature 210 °C	>= 20 min @Temperature 410 °F	EN 728
Carbon Black Loading	2.25 %	2.25 %	ISO 6964
Melt Flow	0.43 g/10 min @Load 5.00 kg, Temperature 190 °C	0.43 g/10 min @Load 11.0 lb, Temperature 374 °F	ISO 1133
	10.3 g/10 min @Load 21.6 kg, Temperature 190 °C	10.3 g/10 min @Load 47.6 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	59	59	ISO 868
Tensile Strength, Yield	22.0 MPa @Thickness 2.00 mm	3190 psi @Thickness 0.0787 in	ISO 527-2
Elongation at Yield	8.0 % @Thickness 2.00 mm	8.0 % @Thickness 0.0787 in	ISO 527-2
Tensile Modulus	0.850 GPa @Thickness 2.00 mm	123 ksi @Thickness 0.0787 in	ISO 527-2
Charpy Impact, Notched	0.800 J/cm <sup>2</sup> @Temperature -30.0 °C	3.81 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 179
	2.40 J/cm <sup>2</sup> @Temperature 23.0 °C	11.4 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Vicat Softening Point	70.0 °C @Load 5.10 kg	158 °F @Load 11.2 lb	ISO 306

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 220 °C	374 - 428 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China