

SGL Carbon Group EK 2230 Carbon Graphite

Category : Carbon , Graphite

Material Notes:

Good mechanical strength, good sliding properties, high temperature resistance, high thermal shock resistance, low wettability, high corrosion resistance, high thermal conductivity, high purity, and good electrical conductivity. Typical Applications: High Volume Seals
 Certified for use in potable water and/or in foodstuff
 Information provided by SGL Carbon Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_SGL-Carbon-Group-EK-2230-Carbon-Graphite.php

Physical Properties	Metric	English	Comments
Density	1.85 g/cc	0.0668 lb/in ³	
Open Porosity	<= 2.5 %	<= 2.5 %	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	Size/Load - 10/100
Hardness, Shore C	86	86	
Modulus of Elasticity	22.1 GPa	3200 ksi	
Flexural Strength	58.6 MPa	8500 psi	
Compressive Strength	159 MPa	23000 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	6.48 Åµm/m-Å°C	3.60 Åµin/in-Å°F	
	@Temperature 20.0 Å°C	@Temperature 68.0 Å°F	
Thermal Conductivity	17.3 W/m-K	120 BTU-in/hr-ft ² -Å°F	
Maximum Service Temperature, Air	204 Å°C	400 Å°F	In oxygen
Maximum Service Temperature, Inert	204 Å°C	399 Å°F	Reducing Atm.

Descriptive Properties	Value	Comments
Impregnation	Resin	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China