

SK Chemicals SKYTHANE[®] S368D Polyester Based Thermoplastic Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

Material Notes:

Description: SK Chemicals has supplied Thermoplastic Polyurethane Elastomer (TPU) under the name of SKYTHANE. Applications include: Keyboard Covers, Outsoles of Soccer Shoes, Wire and Cable, Airbags, Sheets and Film, Hoses and Tubing, Shoe Components, Fire Hoses. Information provided by SK Chemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SK-Chemicals-SKYTHANE-S368D-Polyester-Based-Thermoplastic-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68	68	ASTM D2240
Tensile Strength, Ultimate	44.1 MPa	6400 psi	ASTM D412
Elongation at Break	430 %	430 %	ASTM D412
100% Modulus	0.0255 GPa	3.70 ksi	ASTM D412
300% Modulus	0.0352 GPa	5.10 ksi	ASTM D412
Resilience	43	43	Vertical Rebound; ASTM D2632
Tear Strength	216 kN/m	1230 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	95	95	H18 wheel, 1000g load; ASTM D1044

Thermal Properties	Metric	English	Comments
Vicat Softening Point	125 Å°C	257 Å°F	ASTM D1525

Processing Properties	Metric	English	Comments
Processing Temperature	210 Å°C	410 Å°F	Transition Temperature
	210 Å°C	410 Å°F	Metering Temperature
Middle Barrel Temperature	205 Å°C	401 Å°F	
Nozzle Temperature	215 Å°C	419 Å°F	

Mold Temperature Processing Properties	20.0 - 40.0 Å°C Metric	68.0 - 104 Å°F English	Comments
---	---------------------------	---------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China