

SSAB Tunnplat Domex® 024 BOR Water quenched Boron Steel

Category: Metal, Ferrous Metal, Alloy Steel, Low Alloy Steel

Material Notes:

Domex® is the brand name of hot rolled products from SSAB Tunnplat. Compared to conventional quenched and tempered steels, boron steel have several benefits including better formability. Boron steels are used for a wide variety of applications - as a wear material and as a high-strength structural steel. Examples include wear plate, screen plate, punching tools, spades, knives, saw blades, caterpillar tracks, and agricultural machinery. Data provided by SSAB Tunnplat.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SSAB-Tunnplat-Domex-024-BOR-Water-quenched-Boron-Steel.php

Physical Properties	Metric	English	Comments
Density	7.87 g/cc	0.284 lb/in³	Estimated by MatWeb

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	490	490	HV ₁₀ ; approximate
Tensile Strength, Ultimate	1600 MPa	232000 psi	
Tensile Strength, Yield	1200 MPa	174000 psi	
Elongation at Break	10 %	10 %	A ₅
Impact	25	25	J/cm²; -20°C
	35	35	J/cm²; 20°C

Component Elements Properties	Metric	English	Comments
Boron, B	0.0030 %	0.0030 %	
Carbon, C	0.20 - 0.25 %	0.20 - 0.25 %	
Chromium, Cr	0.15 - 0.25 %	0.15 - 0.25 %	
Iron, Fe	98 %	98 %	As Remainder
Manganese, Mn	1.0 - 1.3 %	1.0 - 1.3 %	
Phosphorous, P	<= 0.030 %	<= 0.030 %	
Silicon, Si	0.20 - 0.35 %	0.20 - 0.35 %	
Sulfur, S	<= 0.025 %	<= 0.025 %	

Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China