

## SSAB Tunplatt Domex® 034 BOR Rolled Boron Steel

Category : Metal , Ferrous Metal , Alloy Steel , Low Alloy Steel

**Material Notes:**

Domex® is the brand name of hot rolled products from SSAB Tunplatt. Compared to conventional quenched and tempered steels, boron steel have several benefits including better formability. Boron steels are used for a wide variety of applications - as a wear material and as a high-strength structural steel. Examples include wear plate, screen plate, punching tools, spades, knives, saw blades, caterpillar tracks, and agricultural machinery. Data provided by SSAB Tunplatt.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SSAB-Tunplatt-Domex-034-BOR-Rolled-Boron-Steel.php](http://www.lookpolymers.com/polymer_SSAB-Tunplatt-Domex-034-BOR-Rolled-Boron-Steel.php)

Physical Properties	Metric	English	Comments
Density	7.87 g/cc	0.284 lb/in <sup>3</sup>	Estimated by MatWeb

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	180	180	HV <sub>10</sub> ; approximate
Tensile Strength, Ultimate	600 MPa	87000 psi	
Tensile Strength, Yield	370 MPa	53700 psi	
Elongation at Break	25 %	25 %	A <sub>5</sub>

Component Elements Properties	Metric	English	Comments
Boron, B	0.0030 %	0.0030 %	
Carbon, C	0.25 - 0.30 %	0.25 - 0.30 %	
Chromium, Cr	0.15 - 0.25 %	0.15 - 0.25 %	
Iron, Fe	98 %	98 %	As Remainder
Manganese, Mn	1.0 - 1.3 %	1.0 - 1.3 %	
Phosphorous, P	<= 0.030 %	<= 0.030 %	
Silicon, Si	0.20 - 0.35 %	0.20 - 0.35 %	
Sulfur, S	<= 0.025 %	<= 0.025 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China