

## SSAB Tunplatt Domex® 700MC HSLA Steel

Category : Metal , Ferrous Metal , Alloy Steel , Low Alloy Steel

### Material Notes:

HSLA Steel Characteristics: Domex® MC grade steels conform to the provisions of EN 10149-2 standard and often have better properties. Property data is for hot-rolled steel. Domex® is the brand name of hot rolled products from SSAB Tunplatt. Domex® cold-forming steels are modern structural steels. General use of Domex® high strength steels offers a number of benefits compared to ordinary structural steels: Lower weight, Simpler production, Lower creep rate, Longer useful life, Higher load-bearing capacity, Lower transport costs, Reduced stocks, Lower overall cost. Data provided by SSAB Tunplatt.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SSAB-Tunplatt-Domex-700MC-HSLA-Steel.php](http://www.lookpolymers.com/polymer_SSAB-Tunplatt-Domex-700MC-HSLA-Steel.php)

Physical Properties	Metric	English	Comments
Density	7.87 g/cc	0.284 lb/in <sup>3</sup>	Estimated by MatWeb

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	750 - 950 MPa	109000 - 138000 psi	
Tensile Strength, Yield	>= 700 MPa	>= 102000 psi	
Elongation at Break	>= 10 % @Thickness <=3.00 mm	>= 10 % @Thickness <=0.118 in	A <sub>80</sub>
	>= 12 % @Thickness >=3.00 mm	>= 12 % @Thickness >=0.118 in	A <sub>5</sub>
Impact	71	71	J/cm <sup>2</sup> ; -20°C
	52.0 @Temperature -40.0 °C	52.0 @Temperature -40.0 °F	J/cm <sup>2</sup>
Bend Radius, Minimum	>= 1.0 t	>= 1.0 t	t<3mm; internal bend radius, 90°
	>= 1.5 t	>= 1.5 t	3 mm < t < 6mm; internal bend radius, 90°
	>= 2.0 t	>= 2.0 t	t>6mm; internal bend radius, 90°

Component Elements Properties	Metric	English	Comments
Aluminum, Al	>= 0.015 %	>= 0.015 %	
Boron, B	<= 0.0050 %	<= 0.0050 %	
Carbon, C	<= 0.12 %	<= 0.12 %	

Component Elements Properties	Metric	English	Comments
Manganese, Mn	<= 2.1 %	<= 2.1 %	
Molybdenum, Mo	<= 0.50 %	<= 0.50 %	
Phosphorous, P	<= 0.025 %	<= 0.025 %	
Silicon, Si	<= 0.30 %	<= 0.30 %	
Sulfur, S	<= 0.010 %	<= 0.010 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China