

STAR Thermoplastic Alloys & Rubbers StarTUFF TF 55-HR-1 TPE

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Product Description: StarTUFF TF 55-HR-1 is an easy processing TPE designed for injection molding Features:Soft TouchRubbery FeelHigh Tear strengthHigh Tensile strengthProcessing Method: Injection MoldingInformation Provided by STAR Thermoplastic Elastomers

Order this product through the following link:

http://www.lookpolymers.com/polymer_STAR-Thermoplastic-Alloys-Rubbers-StarTUFF-TF-55-HR-1-TPE.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.940 g/cc	0.940 g/cc	ASTM D792
Viscosity	13900 cP	13900 cP	ASTM D3835
	@Shear Rate 10994 1/s, Temperature 210 Â°C	@Shear Rate 10994 1/s, Temperature 410 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	ASTM D2240
	@Time 10.0 sec	@Time 0.00278 hour	
Tensile Strength at Break	7.45 MPa	1080 psi	Die C; ASTM D414
	@Time 7200 sec	@Time 2.00 hour	
Elongation at Break	750 %	750 %	Die C; ASTM D412
	@Time 7200 sec	@Time 2.00 hour	
300% Modulus	0.00153 GPa	0.222 ksi	Die C; ASTM D412
	@Time 7200 sec	@Time 2.00 hour	
Tear Strength	31.2 kN/m	178 pli	ASTM D624

Descriptive Properties	Value	Comments
Color	Natural	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China