

Saint-Gobain CHR® 2345-1 Polyimide Film Backing Silicone Adhesive Pressure Sensitive Tape

Category: Polymer, Tape, Thermoset, Polyimide, TS, Silicone

Material Notes:

Description: Polyimide films are employed because of their extreme heat resistance. Service temperatures range from -100°F to 500°F (-73°C to 260°C). These flame retardant films exhibit high tensile strength and conformability, good solvent resistance, excellent dielectric strength and good abrasion resistance. Polyimide tape applications include electrical insulation, capacitor, transformer and coil wrapping, electronic assembly, and wave solder protection. This tape uses a silicone adhesive system. Perfect for extreme temperature applications, silicone adhesives perform in continuous operating temperatures from -100°F to 500° (-73°C to 260°C). Silicone-based adhesive systems exhibit good chemical resistance, retain electrical properties, and remove cleanly with little or no residue. Specification Notes: UL Guide OANZ2, File E66639, UL510. All data based on a 0.0025 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .001 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Saint-Gobain-CHR-2345-1-Polyimide-Film-Backing-Silicone-Adhesive-Pressure-Sensitive-Tape.php

Mechanical Properties	Metric	English	Comments
Elongation at Break	50 %	50 %	
Tear Strength	5.26 kN/m	30.0 pli	Initial Tear Strength

Thermal Properties	Metric	English	Comments	
Maximum Service Temperature, Air	260 °C	500 °F		
Minimum Service Temperature, Air	-73.3 °C	-100 °F		

Electrical Properties	Metric	English	Comments
Dielectric Strength	102 kV/mm	2600 kV/in	
Dielectric Breakdown	6500 V	6500 V	

Descriptive Properties	Value	Comments	
Color	Amber		

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058



Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China