

## Saint-Gobain CHR® M706 Polyester Film Backing Acrylic Adhesive Pressure Sensitive Tape

Category: Polymer, Tape

## **Material Notes:**

Description: Polyester films have excellent dimensional stability, high tensile, tear, and impact strengths, and ultimate elongation up to 120% of its original dimensions. These films exhibit low water absorption and good resistance to oils, greases, strong acids, and organic solvents. They also retain electrical properties, dielectric strength, and dielectric constant in continuous operating temperatures from - 100ŰF to 350ŰF (-73ŰC to 177ŰC). Applications include transformer and capacitor wrapping, printed circuit board fabrication, splicing tapes, composite bonding protection, and low-cost masking. This tape uses an acrylic adhesive system. Acrylic adhesves perform in continuous operating temperatures from -40ŰF to +375ŰF (-40ŰC to +188ŰC). Benefits include exceptional solvent resistance, excellent adhesion to metal, superior weathering and aging characteristics. Acrylics have an excellent shelf life, and when exposed to elevated temperatures, their ability to wet-out improves thus increasing both adhesion and tack properties. WHITE in color. Specification Notes: UL Guide OANZ2, File E51201, UL510All data based on a 0.0025 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .001 inches.) Information provided by Saint Gobain Performance Products.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Saint-Gobain-CHR-M706-Polyester-Film-Backing-Acrylic-Adhesive-Pressure-Sensitive-Tape.php

| Mechanical Properties | Metric    | English  | Comments              |
|-----------------------|-----------|----------|-----------------------|
| Elongation at Break   | 100 %     | 100 %    |                       |
| Tear Strength         | 4.38 kN/m | 25.0 pli | Initial Tear Strength |

| Thermal Properties               | Metric   | English  | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 163 °C   | 325 °F   |          |
| Minimum Service Temperature, Air | -28.9 °C | -20.0 °F |          |

| Electrical Properties | Metric     | English    | Comments |
|-----------------------|------------|------------|----------|
| Dielectric Strength   | 78.7 kV/mm | 2000 kV/in |          |
| Dielectric Breakdown  | 5000 V     | 5000 V     |          |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Color                  | White |          |

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842



Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China