

## Saint-Gobain CHR® SG03-06(R) Premium Glass-PTFE Backing Acrylic Adhesive Pressure Sensitive Tape

Category: Polymer, Adhesive, Tape, Thermoplastic, Acrylic (PMMA)

## **Material Notes:**

Description: PTFE glass provide dimensional stability, high tensile strength and edge tear, operates over a temperature range from -100°F to +500°F (-73°C to 260°C), and offers better abrasion resistance than uncoated glass cloth. The PTFE surface offers quick release and chemical resistance characteristics. Anti-static PTFE glass yields improved thermal conductivity and static dissipation. Available with silicone or acrylic adhesives, PTFE glass applications include heat sealing and low friction release surface liners for conveyors. This tape uses an acrylic adhesive system. Acrylic adhesves perform in continuous operating temperatures from -40°F to +375°F (-40°C to +188°C). Benefits include exceptional solvent resistance, excellent adhesion to metal, superior weathering and aging characteristics. Acrylics have an excellent shelf life, and when exposed to elevated temperatures, their ability to wet-out improves thus increasing both adhesion and tack properties. Specification Notes: 21CFR175.105 and 21CFR177.1550 compliant. All data based on a 0.0077 inch test sample. (Thickness given is for both backing and adhesive. Backing thickness is .006 inches.) Information provided by Saint Gobain Performance Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Saint-Gobain-CHR-SG03-06R-Premium-Glass-PTFE-Backing-Acrylic-Adhesive-Pressure-Sensitive-Tape.php

| Mechanical Properties | Metric    | English  | Comments              |
|-----------------------|-----------|----------|-----------------------|
| Elongation at Break   | <= 5.0 %  | <= 5.0 % |                       |
| Tear Strength         | 30.7 kN/m | 175 pli  | Initial Tear Strength |

| Thermal Properties               | Metric   | English | Comments |  |
|----------------------------------|----------|---------|----------|--|
| Maximum Service Temperature, Air | 260 °C   | 500 °F  |          |  |
| Minimum Service Temperature, Air | -73.3 °C | -100 °F |          |  |

| Electrical Properties | Metric     | English    | Comments |
|-----------------------|------------|------------|----------|
| Dielectric Strength   | 51.2 kV/mm | 1300 kV/in |          |
| Dielectric Breakdown  | 6500 V     | 6500 V     |          |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Color                  | Brown |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China