

## Saint-Gobain COHRLastic® 9235 High Performance Silicone Solid Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

### Material Notes:

Description: COHRLastic® solid silicone rubber in square sheet and continuous length form has a smooth, blemish-free surface. It is available in degrees of hardness from relatively soft 30 durometer to the relatively hard 70 durometer on the Shore A scale. It is manufactured in different formulations to provide a choice of physical properties and cost considerations. 9200 Series: COHRLastic 9200 High Performance Series provides excellent tensile strength and superior tear resistance. It is tougher and more resilient than general-purpose silicone. Standard thicknesses are 1/32", 1/16" and 1/8", and it withstands temperatures ranging from -100°F to +400°F. A minimum thickness of 0.015" is available on a minimum quantity basis. All data based on a 0.0625 inch test sample. (Also comes in thicknesses from 1/32" to 1/8") Information provided by Saint Gobain Performance Products.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Saint-Gobain-COHRLastic-9235-High-Performance-Silicone-Solid-Rubber.php](http://www.lookpolymers.com/polymer_Saint-Gobain-COHRLastic-9235-High-Performance-Silicone-Solid-Rubber.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	25 - 35	25 - 35	Increases by 10 after dry heat aging for 70 hrs at 437°F.; ASTM D2240
Tensile Strength, Yield	7.93 MPa	1150 psi	Tensile strength decreases by 15% after dry heat aging for 70 hrs at 437°F.; ASTM D412
Elongation at Break	800 %	800 %	Elongation properties decrease by 30% after dry heat aging for 70 hrs at 437°F.; ASTM D412
Tear Strength	26.3 kN/m	150 pli	Initial Tear Strength; ASTM D624
Compression Set	30 % @Temperature 160 °C	30 % @Temperature 320 °F	Constant Deflection, 70 hrs.; ASTM D395

Thermal Properties	Metric	English	Comments
CTE, linear	270 µm/m-°C @Temperature 20.0 °C	150 µin/in-°F @Temperature 68.0 °F	
Specific Heat Capacity	1.26 J/g-°C	0.300 BTU/lb-°F	
Thermal Conductivity	0.187 W/m-K	1.30 BTU-in/hr-ft²-°F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Color Descriptive Properties	Grav Value	Comments
---------------------------------	---------------	----------

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)  
Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)  
Tel : +86 021-51131842  
Mobile : +86 13061808058  
Skype : lookpolymers  
Address : United North Road 215,Fengxian District, Shanghai City,China