

Samsung Cheil Industries Starex[®] LX-0981 ABS, Unreinforced Metallic-Look

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Luminous Grade - gives aesthetics of a painted surface without painting. Reduces time, cost, and environmental hazards (such as solvents). Information provided by Samsung Cheil Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-LX-0981-ABS-Unreinforced-Metallic-Look.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Melt Flow	21 g/10 min	21 g/10 min	ASTM D1238
	@Load 10.0 kg, Temperature 220 Å°C	@Load 22.0 lb, Temperature 428 Å°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D785
Tensile Strength at Break	32.4 MPa	4700 psi	50 mm/min; ASTM D638
Tensile Strength, Yield	46.1 MPa	6680 psi	50 mm/min; ASTM D638
Elongation at Break	17 %	17 %	50 mm/min; ASTM D638
Tensile Modulus	2.26 GPa	327 ksi	50 mm/min; ASTM D638
Flexural Strength	64.7 MPa	9380 psi	2.8 mm/min; ASTM D790
Flexural Modulus	2.35 GPa	341 ksi	2.8 mm/min; ASTM D790
Izod Impact, Notched	2.06 J/cm	3.86 ft-lb/in	ASTM D256
	@Thickness 6.35 mm	@Thickness 0.250 in	
	2.06 J/cm	3.86 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	93.0 Å°C	199 Å°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	84.0 Å°C	183 Å°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	96.0 Å°C	205 Å°F	B/50; ISO R306

Thermal Properties	Metric 	English	Comments 
Flammability, UL94	HB @Thickness 1.50 - 3.00 mm	HB @Thickness 0.0591 - 0.118 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China