

## Samsung Cheil Industries Starex<sup>®</sup> TX-0530T TRABS, Unreinforced

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Transparent, Molded

**Material Notes:**

Information provided by Samsung Cheil Industries.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Samsung-Cheil-Industries-Starex-TX-0530T-TRABS-Unreinforced.php](http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-TX-0530T-TRABS-Unreinforced.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.08 g/cc	1.08 g/cc	ASTM D792
Melt Flow	13 g/10 min @Load 10.0 kg, Temperature 220 Å°C	13 g/10 min @Load 22.0 lb, Temperature 428 Å°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	101.6	101.6	ASTM D785
Tensile Strength, Yield	41.2 MPa	5970 psi	5 mm/min; ASTM D638
Izod Impact, Notched	1.67 J/cm @Thickness 3.17 mm	3.12 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	86.0 Å°C	187 Å°F	B/50; ISO R306

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China