

Samyang Triel® 5500 Thermoplastics Polyetherester Elastomer, General Extrusion

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester, TP , Polyether Ester Elastomer

Material Notes:

Excellent mechanical characteristics, elasticity, thermal resistance and chemical resistance.5500 is an extrusion grade.Information provided by Samyang.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Triel-5500-Thermoplastics-Polyetherester-Elastomer-General-Extrusion.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Water Absorption	0.50 %	0.50 %	ASTM D570
Linear Mold Shrinkage	0.015 - 0.017 cm/cm	0.015 - 0.017 in/in	ASTM D955
Melt Flow	15 g/10 min	15 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	
	15 g/10 min	15 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 240 °C	@Load 4.76 lb, Temperature 464 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50	50	ASTM D2240
Tensile Strength, Ultimate	24.5 MPa	3560 psi	ASTM D638
Tensile Strength, Yield	9.81 MPa	1420 psi	ASTM D638
	@Strain 5.00 %	@Strain 5.00 %	
	12.7 MPa	1850 psi	ASTM D638
	@Strain 10.0 %	@Strain 10.0 %	
	15.7 MPa	2280 psi	ASTM D638
	@Strain 50.0 %	@Strain 50.0 %	
Flexural Yield Strength	7.85 MPa	1140 psi	ASTM D790
Flexural Modulus	0.145 GPa	21.1 ksi	ASTM D790
Izod Impact, Notched	NB	NB	ASTM D256
	@Thickness 3.17 mm, Temperature -40.0 °C	@Thickness 0.125 in, Temperature -40.0 °F	

Mechanical Properties	Metric	English	Comments
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	210 °C	410 °F	ASTM D2117
Deflection Temperature at 0.46 MPa (66 psi)	87.0 °C	189 °F	ASTM D648
Vicat Softening Point	174 °C	345 °F	ASTM D1525

Descriptive Properties	Value	Comments
Flexible Rate	> 400%	ASTM D638

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China