

Samyang Triloy[®] 120H PC/ABS alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Characteristics: Impact resistant, Chemical resistant, Dimensional stability, Processability, Good flow
 Applications: Automotive bumper, Automotive outdoor handle
 All information provided by Samyang

Order this product through the following link:

http://www.lookpolymers.com/polymer_Samyang-Triloy-120H-PCABS-alloy.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 250 °C	@Load 8.38 lb, Temperature 482 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Yield	53.0 MPa	7680 psi	ASTM D638
Elongation at Break	150 %	150 %	ASTM D638
Flexural Yield Strength	63.7 MPa	9250 psi	ASTM D790
Flexural Modulus	1.72 GPa	249 ksi	ASTM D790
Izod Impact, Unnotched	7.35 J/cm	13.8 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear	83.0 µm/m-°C	46.1 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	104 °C	219 °F	ASTM D648
Flammability, UL94	HB	HB	
	@Thickness 1.59 mm	@Thickness 0.0625 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	5.00e+16 ohm-cm	5.00e+16 ohm-cm	ASTM D257

Electrical Properties	Metric	English	Comments
Dielectric Constant	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	23.0 kV/mm	584 kV/in	ASTM D149
Dissipation Factor	0.0090 @Frequency 1.00e+6 Hz	0.0090 @Frequency 1.00e+6 Hz	ASTM D150
Arc Resistance	118 sec	118 sec	ASTM D495

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	230 - 250 Å°C	446 - 482 Å°F	
Middle Barrel Temperature	220 - 240 Å°C	428 - 464 Å°F	
Front Barrel Temperature	210 - 230 Å°C	410 - 446 Å°F	
Nozzle Temperature	240 - 250 Å°C	464 - 482 Å°F	
Melt Temperature	240 - 250 Å°C	464 - 482 Å°F	
Drying Temperature	120 Å°C	248 Å°F	
Dry Time	3 - 5 hour	3 - 5 hour	
Moisture Content	<= 0.020 %	<= 0.020 %	
Screw Speed	30 - 80 rpm	30 - 80 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China