

ScanTube THV Tubing

Category : Polymer , Thermoplastic , Fluoropolymer

Material Notes:

Information provided by ScanTube, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ScanTube-THV-Tubing.php

Physical Properties	Metric	English	Comments
Density	1.97 g/cc	0.0712 lb/in ³	ASTM D792
Water Absorption	<= 0.010 %	<= 0.010 %	ASTM D257

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	45	45	ASTM D2240
Tensile Strength	29.6 MPa	4300 psi	ASTM D638, ASTM D1708
Elongation at Break	500 %	500 %	ASTM D638, ASTM D1708
Tensile Modulus	0.207 GPa	30.0 ksi	ASTM D638
Flexural Modulus	1.24 GPa	180 ksi	ASTM D790
Compressive Strength	12.4 MPa	1800 psi	ASTM D695
Izod Impact, Notched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.202 W/m-K	1.40 BTU-in/hr-ft ² - °F	ASTM C177
Melting Point	125 - 185 °C	257 - 365 °F	
Maximum Service Temperature, Air	120 °C	248 °F	Continuous
Deflection Temperature at 0.46 MPa (66 psi)	31.0 - 37.0 °C	87.8 - 98.6 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	28.0 - 32.0 °C	82.4 - 89.6 °F	ASTM D648
Flammability, UL94	V-0	V-0	
Oxygen Index	>= 65 %	>= 65 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	ASTM D257

Electrical Properties	Metric	English	Comments
Dielectric Constant	@Frequency 1000 Hz	@Frequency 1000 Hz	ASTM D150
	4.2	4.2	ASTM D150
Dielectric Strength	0.709 kV/mm	18.0 kV/in	Short Term; 10 mil film; ASTM D149
	0.12	0.12	ASTM D150
Dissipation Factor	@Frequency 1000 Hz	@Frequency 1000 Hz	ASTM D150
	0.17	0.17	ASTM D150
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	ASTM D150

Descriptive Properties	Value	Comments
Chemical Resistance	Good	
Weather Resistance	Excellent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China