

Schott GM32087 Dental Glass

Category : Ceramic , Glass , Oxide , Silicon Oxide

Material Notes:

Remarks: Sr-containing, low refractive glass
 Application: Composite
 Advantages: Greater variety of composition and refractive indices
 Outstanding transparency
 Best radiopacities
 Information Provided by SCHOTT North America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Schott-GM32087-Dental-Glass.php

Physical Properties	Metric	English	Comments
Density	2.60 g/cc	0.0939 lb/in ³	

Thermal Properties	Metric	English	Comments
CTE, linear	4.00 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature -30.0 - 70.0 $\text{Å}^\circ\text{C}$	2.22 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature -22.0 - 158 $\text{Å}^\circ\text{F}$	
Transformation Temperature, Tg	680 $\text{Å}^\circ\text{C}$	1260 $\text{Å}^\circ\text{F}$	ISO 7884-8

Optical Properties	Metric	English	Comments
Refractive Index	1.52	1.52	n _d

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	15 %	15 %	
B ₂ O ₃	15 %	15 %	
BaO	1.0 %	1.0 %	
SiO ₂	50 %	50 %	

Descriptive Properties	Value	Comments
Hydrolytic Resistance	Class 1	DIN ISO 719
Radiopacity (digital method)	370	ISO 4049
Radiopacity as thickness of aluminium equal to 2-mm thick glass material	4.2 (210%)	ISO 4049
SrO (%)	20	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China