

## Schwartz Technical Plastics LAMINEX® 2101 Cotton Fabric, Phenolic Resin Impregnated

Category : Polymer , Thermoset , Phenolic , Phenolic, Novolac, Fabric Filled

### Material Notes:

Application: bearing segments and prismatic bearings  
Information provided by Schwartz Technical Plastics GmbH

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Schwartz-Technical-Plastics-LAMINEX-2101-Cotton-Fabric-Phenolic-Resin-Impregnated.php](http://www.lookpolymers.com/polymer_Schwartz-Technical-Plastics-LAMINEX-2101-Cotton-Fabric-Phenolic-Resin-Impregnated.php)

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	ISO R 1183
Water Absorption at Saturation	2.2 % @Temperature 20.0 °C	2.2 % @Temperature 68.0 °F	ISO R 62

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	130 MPa	18900 psi	Hc 30; ISO 2039; partially
Tensile Strength, Yield	40.0 - 60.0 MPa	5800 - 8700 psi	ISO-DIS 527
Flexural Strength	60.0 MPa	8700 psi	DIN 54352
Flexural Modulus	7.00 - 10.0 GPa	1020 - 1450 ksi	DIN 53457
Compressive Strength	140 MPa	20300 psi	ISO 604
Izod Impact, Notched (ISO)	>= 8.00 kJ/m <sup>2</sup>	>= 3.81 ft-lb/in <sup>2</sup>	DIN 53453
Izod Impact Resistance	>= 0.800 J/cm <sup>2</sup>	>= 3.81 ft-lb/in <sup>2</sup>	swinging hammer 0,1 DIN 51222; DIN 53453

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 - 40.0 µm/m-°C @Temperature 20.0 - 100 °C	16.7 - 22.2 µin/in-°F @Temperature 68.0 - 212 °F	DIN 53752
Thermal Conductivity	0.300 W/m-K	2.08 BTU-in/hr-ft <sup>2</sup> - °F	DIN 52612
Maximum Service Temperature, Air	125 °C	257 °F	Continuous
	150 °C	302 °F	Intermittent

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+9 ohm-cm	1.00e+9 ohm-cm	DIN 53482

Electrical Properties	Metric	English	Comments
Dielectric Constant	6.0 - 10 @Frequency 1000 Hz	6.0 - 10 @Frequency 1000 Hz	DIN 53483
Dielectric Strength	20.0 kV/mm	508 kV/in	DIN 53481
Dielectric Loss Index	0.40 @Frequency 1000 Hz	0.40 @Frequency 1000 Hz	DIN 53483

Descriptive Properties	Value	Comments
Moisture Absorption at Equilibrium	300 mg	DIN 53472

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China