

Shandong Rike Chemical HELIâ, ¢ HL-750 Weather-resistance Acrylic Impact Modifier (AIM)

Category: Other Engineering Material, Additive/Filler for Polymer, Polymer

Material Notes:

Outline of ACR Impact Modifiers: The PVC impact modifiers developed by our company are acrylic copolymers (ACR) with a core-shell structure, their cores are acrylic ester and shells are methacrylic copolymers. The basic functions of our impact modifiers are to improve the impact performance of PVC products to meet the requirements of engineering plastics and simultaneously increase their heat and light stability. Information Provided by Shandong Rike Chemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shandong-Rike-Chemical-HELI-HL-750-Weather-resistance-Acrylic-Impact-Modifier-AIM.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------------|------------------------|----------|
| Bulk Density | 0.350 - 0.550 g/cc | 0.0126 - 0.0199 lb/in³ | |
| Volatiles | <= 1.0 % | <= 1.0 % | |
| Particle Mesh Size | 30 Mesh | 30 Mesh | <2% |

| Mechanical Properties | Metric | English | Comments |
|------------------------------|---|--|----------|
| | 45.6 MPa | 6610 psi | |
| Tensile Strength | @Temperature 18.0 °C, Time 86400 sec | @Temperature 64.4 °F, Time 24.0 hour | |
| Izod Impact, Unnotched (ISO) | 28.1 kJ/m² | 13.4 ft-lb/in² | |
| | @Temperature 0.000 °C, Time 86400 sec | @Temperature 32.0 °F, Time 24.0 hour | |

| Thermal Properties | Metric | English | Comments |
|-----------------------|---------------|---------------|----------|
| Vicat Softening Point | 84.9 °C | 185 °F | |
| | @Load 5.00 kg | @Load 11.0 lb | |

| Descriptive Properties | Value | Comments |
|------------------------|--------------|----------|
| Appearance | White powder | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842



Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China