

Shandong Rike Chemical HELI,ç HL-766 Weather-resistance Acrylic Impact Modifier (AIM)

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer

Material Notes:

Outline of ACR Impact Modifiers: The PVC impact modifiers developed by our company are acrylic copolymers (ACR) with a core-shell structure, their cores are acrylic ester and shells are methacrylic copolymers. The basic functions of our impact modifiers are to improve the impact performance of PVC products to meet the requirements of engineering plastics and simultaneously increase their heat and light stability. Information Provided by Shandong Rike Chemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shandong-Rike-Chemical-HELI-HL-766-Weather-resistance-Acrylic-Impact-Modifier-AIM.php

Physical Properties	Metric	English	Comments
Bulk Density	0.350 - 0.550 g/cc	0.0126 - 0.0199 lb/in ³	
Volatiles	<= 1.0 %	<= 1.0 %	
Particle Mesh Size	30 Mesh	30 Mesh	<2%

Mechanical Properties	Metric	English	Comments
Tensile Strength	47.2 MPa @Temperature 18.0 °C, Time 86400 sec	6850 psi @Temperature 64.4 °F, Time 24.0 hour	
Izod Impact, Unnotched (ISO)	27.8 kJ/m ² @Temperature 0.000 °C, Time 86400 sec	13.2 ft-lb/in ² @Temperature 32.0 °F, Time 24.0 hour	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	84.5 °C @Load 5.00 kg	184 °F @Load 11.0 lb	

Descriptive Properties	Value	Comments
Appearance	White powder	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China