

Shinkong Synthetic Fibers Shinite® PP4210 PP, Fire Retardant

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Flame Retardant

Material Notes:

Information from Shinkong Synthetic Fibers Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Shinkong-Synthetic-Fibers-Shinite-PP4210-PP-Fire-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.930 g/cc	0.930 g/cc	ASTM D792
Water Absorption	0.050 %	0.050 %	ASTM D570
Linear Mold Shrinkage, Flow	0.015 - 0.016 cm/cm	0.015 - 0.016 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.015 - 0.016 cm/cm	0.015 - 0.016 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	30.4 MPa	4410 psi	ASTM D638
Elongation at Break	20 %	20 %	ASTM D638
Flexural Yield Strength	33.3 MPa	4840 psi	ASTM D790
Flexural Modulus	0.981 GPa	142 ksi	ASTM D790
Izod Impact, Notched	0.343 J/cm @Thickness 3.17 mm, Temperature 23.0 Å°C	0.643 ft-lb/in @Thickness 0.125 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	115 Å°C	239 Å°F	ASTM D648
Flammability, UL94	V-2	V-2	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China