

## Shinkong Synthetic Fibers Shinite<sup>®</sup> T101G36 PET, 36% Glass Filled

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 40% Glass Reinforced

**Material Notes:**

Information from Shinkong Synthetic Fibers Corp.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Shinkong-Synthetic-Fibers-Shinite-T101G36-PET-36-Glass-Filled.php](http://www.lookpolymers.com/polymer_Shinkong-Synthetic-Fibers-Shinite-T101G36-PET-36-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.63 g/cc	1.63 g/cc	ASTM D792
Water Absorption	0.15 %	0.15 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	137 MPa	19900 psi	ASTM D638
Elongation at Break	3.6 %	3.6 %	ASTM D638
Flexural Yield Strength	216 MPa	31300 psi	ASTM D790
Flexural Modulus	9.81 GPa	1420 ksi	ASTM D790
Izod Impact, Notched	0.932 J/cm @Thickness 3.17 mm, Temperature 23.0 Å°C	1.74 ft-lb/in @Thickness 0.125 in, Temperature 73.4 Å°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	220 Å°C	428 Å°F	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	4.0	4.0	ASTM D150
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China