

Sibur 21230 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Compounding for stabilization 16K, 16V, 16N, 16M, 16H superior quality. For production of technical and domestic products of complicated profile, of non-woven materials.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sibur-21230-Polypropylene.php

Physical Properties	Metric	English	Comments
Melt Index of Compound	21 - 25 g/10 min	21 - 25 g/10 min	
Ash	<= 0.035 %	<= 0.035 %	For compounding of stabilization of 16M and painted marks are not normalized
Collected Volatile Condensable Material	<= 0.090 %	<= 0.090 %	

Descriptive Properties	Value	Comments
Mass Share of Isotactic Fraction	Non-normalized	
Number of Inclusions	<3 pcs	
Spread Flow Batch Error	<±8 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China