

## Sibur PVC S-6558-U-LP Suspension Polyvinyl Chloride (PVC)

Category : Polymer , Thermoplastic , Vinyl (PVC)

**Material Notes:**

For production of plasticized and rigid articles of general purpose.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Sibur-PVC-S-6558-U-LP-Suspension-Polyvinyl-Chloride-PVC.php](http://www.lookpolymers.com/polymer_Sibur-PVC-S-6558-U-LP-Suspension-Polyvinyl-Chloride-PVC.php)

Physical Properties	Metric	English	Comments
Density	0.450 - 0.550 g/cc	0.0163 - 0.0199 lb/in <sup>3</sup>	
Collected Volatile Condensable Material	<= 0.30 %	<= 0.30 %	Moisture and volatile matters

Thermal Properties	Metric	English	Comments
Decomposition Temperature	>= 160 Â°C	>= 320 Â°F	Thermal stability, for 5 minutes

Descriptive Properties	Value	Comments
K-Value	65-67	
Mass Share of Vinyl Chloride, mln-1	>10	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China