

Sichuan Deyang Haton[®] hCF31 Polyphenylene Sulfide

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS) with 30% Carbon Fiber Filler

Material Notes:

Injection molding Information provided by Sichuan Deyang Chemical Co., LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sichuan-Deyang-Haton-hCF31-Polyphenylene-Sulfide.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	GB/T 1033.1-2008
Water Absorption	0.020 %	0.020 %	GB/T 1034-2008
Linear Mold Shrinkage, Flow	0.0012 cm/cm	0.0012 in/in	GB/T 15585-1995
Linear Mold Shrinkage, Transverse	0.0026 cm/cm	0.0026 in/in	GB/T 15585-1995

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	108	108	GB/T 3398.2-2008
Tensile Strength	176 MPa	25500 psi	GB/T 1040.2-2006
Elongation at Break	0.80 %	0.80 %	GB/T 1040.2-2006
Flexural Strength	256 MPa	37100 psi	GB/T 9341-2008
Flexural Modulus	21.2 GPa	3070 ksi	GB/T 9341-2008
Izod Impact, Notched (ISO)	8.60 kJ/m ²	4.09 ft-lb/in ²	GB/T 1843-2008

Thermal Properties	Metric	English	Comments
Melting Point	280 Â°C	536 Â°F	GBT/T 19466.3-2004
Deflection Temperature at 1.8 MPa (264 psi)	266 Â°C	511 Â°F	GB/T 1634.2-2004
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Insulation Resistance	1.00e+9 ohm	1.00e+9 ohm	GB/T 10064-2006

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China