

Sika Industry SikaFlex 219 LM Low Modulus Polyurethane Sealant

Category : Polymer , Adhesive , Thermoset , Polyurethane, TS , Thermoset Polyurethane, Adhesive

Material Notes:

Sika 219 LM SikaFlex Low Modulus Polyurethane Sealant This is a high performance, low modulus polyurethane base, non-sag elastomeric sealant with excellent adhesion to a wide variety of substrates. Meets Federal Specification TT-S-00230C, Type II, Class A and ASTM C-920, Type S, Grade NS, Class 25 and TT-S-001543A, Type non-sag. 12 - 15 mm Cut-Off. Excellent non-sag. Available in black, white, gray, tan, MB bronze, limestone. Cure Type: Moisture

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sika-Industry-SikaFlex-219-LM-Low-Modulus-Polyurethane-Sealant.php

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0446 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	15 - 25	15 - 25	
Tensile Strength, Ultimate	0.862 MPa	125 psi	
Elongation at Break	>= 700 %	>= 700 %	
Adhesive Bond Strength	0.758 MPa	110 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	76.7 Â°C	170 Â°F	
Minimum Service Temperature, Air	-40.0 Â°C	-40.0 Â°F	

Processing Properties	Metric	English	Comments
Cure Time	360 - 480 min	6.00 - 8.00 hour	Tack-free
Shelf Life	12.0 Month	12.0 Month	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China