

## Silikony Polskie Gumosil M Silicone Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

**Material Notes:**

Flexible with good tearing resistance

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Silikony-Polskie-Gumosil-M-Silicone-Rubber.php](http://www.lookpolymers.com/polymer_Silikony-Polskie-Gumosil-M-Silicone-Rubber.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	Before Curing
Viscosity	45000 cP	45000 cP	Before Curing
Linear Mold Shrinkage	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	After Curing

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	21	21	After Curing
Tensile Strength at Break	4.70 MPa	682 psi	After Curing
Elongation at Break	600 %	600 %	After Curing

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 Â°C	302 Â°F	

Processing Properties	Metric	English	Comments
Cure Time	<= 1440 min	<= 24.0 hour	Curing
Pot Life	90 - 120 min	90 - 120 min	Curing

Descriptive Properties	Value	Comments
Color	White	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China