

## Solvay Specialty Polymers Amodel® FC - 1160 Polyphthalamide (PPA), 60% Glass Fiber

Category : Polymer , Thermoplastic , Polyphthalamide (PPA)

### Material Notes:

Amodel® FC-1160 is an FDA-approved, 60% glass fiber reinforced resin designed for high strength and stiffness. This combines with its excellent thermal properties, low water absorption and good hydrolytic stability to make it particularly suited for components used in food service and consumer applications such as coffee machines and ovens. Features: Chlorine Resistant; Good Chemical Resistance; Good Creep Resistance; Good Dimensional Stability; Good Stiffness; High Stiffness; High Strength; High Temperature Strength; Low Moisture Absorption. Uses: Appliances; Consumer Applications; Filters; Housings; Industrial Applications; Plumbing Parts; Pump Parts; Valves/Valve Parts. Injection Molding Notes: Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding. Information provided by Solvay Specialty Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Solvay-Specialty-Polymers-Amodel-FC-1160-Polyphthalamide-PPA-60-Glass-Fiber.php](http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Amodel-FC-1160-Polyphthalamide-PPA-60-Glass-Fiber.php)

Physical Properties	Metric	English	Comments
Density	1.80 g/cc	0.0650 lb/in <sup>3</sup>	ISO 1183
Filler Content	60 %	60 %	Glass Fiber

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	280 MPa	40600 psi	ISO 527-2
Elongation at Break	1.9 %	1.9 %	ISO 527-2
Tensile Modulus	23.3 GPa	3380 ksi	ISO 527-2
Flexural Strength	438 MPa	63500 psi	ISO 178
Flexural Modulus	22.8 GPa	3310 ksi	ISO 178
Charpy Impact Unnotched	9.00 J/cm <sup>2</sup>	42.8 ft-lb/in <sup>2</sup>	ISO 179
Charpy Impact, Notched	1.30 J/cm <sup>2</sup>	6.19 ft-lb/in <sup>2</sup>	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	298 °C	568 °F	Unannealed; Flatwise; ISO 75-2/A

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	315 - 330 Â°C	599 - 626 Â°F	
Middle Barrel Temperature	320 - 340 Â°C	608 - 644 Â°F	
Front Barrel Temperature	325 - 345 Â°C	617 - 653 Â°F	
Melt Temperature	340 - 360 Â°C	644 - 680 Â°F	
Mold Temperature	160 Â°C	320 Â°F	
Drying Temperature	120 Â°C @Time 14400 sec	248 Â°F @Time 4.00 hour	
Moisture Content	0.030 - 0.060 %	0.030 - 0.060 %	Suggested Max

Descriptive Properties	Value	Comments
Agency Ratings	EU 10/2011; FDA 21 CFR 176.170(c)	
Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	Latin America	
	North America	
Color	Black; Natural	
Form	Pellets	
Processing Technique	Injection Molding	
RoHS Compliance	RoHS Compliant	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China