

Solvay Specialty Polymers Aquivion® D79-20BS Tetrafluoroethylene + SFVE (TFE+SFVE)

Category : Polymer , Thermoplastic , Fluoropolymer

Material Notes:

Aquivion® PFSA dispersions are based on the unique Short Side Chain (SSC) copolymer of Tetrafluoroethylene and a Sulfonyl Fluoride Vinyl Ether (SFVE) $F_2C=CF-O-CF_2CF_2-SO_2F$. The PFSA ionomer dispersions contain its acid form (R-SO₃H) and are available in various solvent systems, EWs and concentrations. Aquivion® PFSA dispersions can be used for the production of PEM fuel cell electrodes, electrochemical cell electrodes, manufacture or repair of ion exchange membranes, super-acid catalyst production or surface treatment of PTFE membranes to improve wetting behavior. Additional Properties: Density - Internal Method (25°C): 1.115 g/cm³; Equivalent Weight (EW) - Internal Method 770 to 810 g/eq; Flammability - No; HSE/Transport Classification - Corrosive; Polymer Concentration - TGA 20 %; Solvent System - >99 % Water, free of ethers. chemically stabilized; Solvent Water Content - > 99 %; Total Acid Capacity - Internal Method 1.23 to 1.30 meq/g; Viscosity - (25°C): 5 to 15 mPa·s. Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Aquivion-D79-20BS-Tetrafluoroethylene-SFVE-TFESFVE.php

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	North America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China