

## Solvay Specialty Polymers Cogegum® AFR/930 Polyolefin, Unspecified (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyolefin

### Material Notes:

Cogegum® HFFR -Halogen Free Fire Retardant compound Polyolefin based thermoplastic compound containing a fire retardant system that contributes to give the cable self-extinguish properties without halogenidric acids evolution; furthermore, toxic and corrosive gases emission and smoke generation are particularly reduced. These characteristics make this compound suitable in all applications where the fire behavior of cable materials is one of the main concerns to be considered in establishing a high safety level in public places. This material complies with RoHS requirements. standard complying - EN 50363-7 TI6; EN 50363-8 TM7; IEC 60502-1 ST8; Cenelec HD 624.7 S1; Cenelec HD 624.6 S1; VDE 0207 HM2, HM5, HJ2; IEC 60092 SHF1

Additional Information: Tests reported are performed on pressed or extruded specimens Coloring - EVA or PE based masterbatches added at 1.2-1.5% by weight; in order to avoid scotching problems during processing, predrying of colour masterbatch is suggested if moisture absorption occurred during storage (4-6 hours at 50-60°C). Storage - The product must be stored under the following conditions: -- closed and undamaged bags -- ambient temperature not exceeding 35°C -- avoid direct exposure to sunlight and weathering - Product alterations could occur due to extended period of storage - Shelf life: 12 months - Solvay Specialty Polymers accepts no liability of any kind in case the above mentioned conditions are not fulfilled. Packaging - 25 kg moisture-resistant bags on 1375 kg pallet - 1000 kg carton box

Extrusion Notes: Extrusion equipment - standard extruders for thermoplastics equipped with low compression screw (1:1.2-1.4 compression ratio and 20-25 L/D ratio are suggested), and an adequate barrel thermoregulation - don't use screw thermoregulation - filter net: not necessary; in case, use 40-80 mesh/cm<sup>2</sup> max. Anyway the use of the breaker plate is advisable, in particular using low compression screws

Information provided by Solvay Specialty Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Solvay-Specialty-Polymers-Cogegum-AFR930-Polyolefin-Unspecified-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Cogegum-AFR930-Polyolefin-Unspecified-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.48 g/cc	1.48 g/cc	ASTM D792
ESCR 10% Igepal®	>= 1000 hour @Thickness 3.00 mm, Temperature 50.0 °C	>= 1000 hour @Thickness 0.118 in, Temperature 122 °F	Condition A, Compression Molded; ASTM D1693
Melt Flow	14 g/10 min @Load 21.6 kg, Temperature 190 °C	14 g/10 min @Load 47.6 lb, Temperature 374 °F	Internal Method

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	42	42	ISO 868
Tensile Strength at Break	10.7 MPa	1550 psi	IEC 60811
Elongation at Break	180 %	180 %	IEC 60811

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Oxygen Index	40 %	40 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.70e+13 ohm-cm	2.70e+13 ohm-cm	IEC 60502
	@Temperature 70.0 °C	@Temperature 158 °F	
Insulation Resistivity	5.40e+14 ohm-cm	5.40e+14 ohm-cm	IEC 60502
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Insulation Resistivity	100 Megaohm/1000 m	328 Megaohm/1000 ft	IEC 60502
	@Temperature 70.0 °C	@Temperature 158 °F	
Insulation Resistivity	2000 Megaohm/1000 m	6560 Megaohm/1000 ft	IEC 60502
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	170 - 180 °C	338 - 356 °F	Collar Temperature
Zone 1	130 - 150 °C	266 - 302 °F	
Zone 2	150 - 170 °C	302 - 338 °F	
Zone 3	160 - 180 °C	320 - 356 °F	
Zone 4	170 - 180 °C	338 - 356 °F	
Die Temperature	180 - 200 °C	356 - 392 °F	
Head Temperature	180 - 190 °C	356 - 374 °F	

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	North America	
Bending Test	Pass	-25°C; IEC 60811
Calorific Potential	16.5 MJ/kg	ISO 1716; Upper (gross)
Cold Impact	Pass	IEC 60811; -25°C
Corrosive Gas in Smoke	< 10.0 µS/mm	Conductivity IEC 60754-2

Descriptive Properties	Value	Comments
Features	Flame Retardant	
	Halogen Free	
	Low Smoke Emission	
	Low Toxicity	
	Self Extinguishing	
Generic	Polyolefin, Unspecified	
Halogenidric Acid Emissions	< 0.10%	
Heat Shock	Pass	IEC 60811; 150°C
Hot Pressure Test	< 50%	80°C; max penetration, K=0.6; IEC 60811
Mechanical Properties After Aging in Air Oven, 100°C, 168 hr	-5	IEC 60811, %Change in Tensile Strength
	-8	IEC 60811, %Change in Tensile Elongation
RoHS Compliance	RoHS Compliant	
Uses	Cable Jacketing	
	Low Voltage Insulation	
	Wire & Cable Applications	
Water Absorption (mg/cm <sup>2</sup> )	1	100°C; 24 hr; IEC 60811
Water Immersion Test, 70°C, 168 hr	0	% Change in Tensile Strength
	-25	% Change in Tensile Elongation

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China