

## Solvay Specialty Polymers Halar® 6914 Polyethylene, Chlorotrifluoroethylene (ECTFE) (Unverified Data\*\*)&l

Category : Polymer , Thermoplastic , Fluoropolymer , ETFE/ECTFE , ECTFE Fluoropolymer

## Material Notes:

Halar® 6914 is a gray, semi-crystalline melt processable fluorinated primer. It is designed to be applied directly to substrates by electrostatic or fluidized bed techniques. In particular Halar® 6914 is recommended for use as a primer on aluminum large surface area parts in protection and anti-corrosion applications. Halar® 6914 provides optimum and rapid bonding and can be used to maximize topcoat adhesion performance in high build coatings specifically. It also exhibits very good thermal and color stability, outstanding permeation and flame resistance and very good chemical resistance. Main features of Halar® 6914 include: - Gray color - Very good thermal and color stability - Optimum and rapid adhesion - Particularly designed for large surface area parts in aluminum - Outstanding permeation resistance - Optimum flame resistance - Very good chemical resistanceAdditional Information: Processing - Halar® 6914 is intended as a primer material to apply directly to substrates. It can be processed using either conventional electrostatic powder coating or fluidized bed equipment. - In the case of electrostatic coating the procedure involves substrate preparation, spray coating, baking and cooling. Several passes maybe required to obtain the desired Halar® load and ensure pin-hole free coatings. Alternatively using fluidized bed equipment preheated items can be coated by dipping directly into the fluidized powder followed by baking. The dipping and baking operation can be repeated to achieve multiple coats and build up the desired coating thickness. - Halar® 6914 can be used neat and without any further formulation. For both techniques, substrate preparation, preheating, coating and baking parameters must all be well controlled to achieve defect free coated items and optimum adhesion. Storage and Handling - Halar® melt processable fluoropolymer resins can be stored without shelf life issues when kept in a clean and dry area at ambient temperatures. Opened containers should be tightly resealed to prevent any contamination. Safety and Toxicology - Before using Halar® melt processable fluoropolymer resins consult the product Material Safety Data Sheet and follow all label directions an handling precautions. - As with all fluoropolymer materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapour or fumes. - See Material Safety Data Sheet for detailed advice on waste disposal methods. Packaging - Halar® 6914 is packaged in 25kg non returnable drums. Each drum has two bags liner made of polyethylene resin.Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Solvay-Specialty-Polymers-Halar-6914-Polyethylene-Chlorotrifluoroethylene-ECTFE-nbspUnverified-Datal.php

| Physical Properties | Metric                               | English                              | Comments             |  |
|---------------------|--------------------------------------|--------------------------------------|----------------------|--|
| Density             | 1.68 g/cc                            | 0.0607 lb/in <sup>3</sup>            | ASTM D3275           |  |
| Particle Size       | 80 µm                                | 80 µm                                | Method C; ASTM D1921 |  |
| Melt Flow           | 7.0 g/10 min                         | 7.0 g/10 min                         |                      |  |
|                     | @Load 2.16 kg,<br>Temperature 275 °C | @Load 4.76 lb,<br>Temperature 527 °F | ASTM D3275           |  |

Thermal Properties Metric English Comments

## SONGHAN Plastic Technology Co., Ltd.

www.lookpolymers.com email:sales@lookpolymers.com

| Melling Point<br>Thermal Properties | 225 °C<br>Metric         | 437 °F<br>English  | Comments |  |  |
|-------------------------------------|--------------------------|--|----------|--|--|
| Descriptive Properties              | Value                    |  | Comments |  |  |
| Appearance                          | Grey                     | Grey   |          |  |  |
| Availability                        | Africa &                 | Africa & Middle East   Asia Pacific   Europe   North America |          |  |  |
|                                     | Asia Pac                 |  |          |  |  |
|                                     | Europe                   |  |          |  |  |
|                                     | North Ar                 |  |          |  |  |
|                                     | South A                  | nerica   |          |  |  |
| Features                            | Bondabi                  | Bondability<br>Good Adhesion                                 |          |  |  |
|                                     | Good Ad                  |  |          |  |  |
|                                     | Good Chemical Resistance |  |          |  |  |
|                                     | Good Co                  | Good Color Stability<br>Good Corrosion Resistance            |          |  |  |
|                                     | Good Co                  |  |          |  |  |
|                                     | Good Th                  | ermal Stability  |          |  |  |
|                                     | Semi Cry                 | Semi Crystalline   |          |  |  |
| Forms                               | Powder                   | Powder   |          |  |  |
| Generic                             | ECTFE                    | ECTFE  |          |  |  |
| Processing Method                   | Coating                  | Coating  |          |  |  |
| Uses                                | Bonding                  | Bonding  |          |  |  |
|                                     | Coating                  | Applications   |          |  |  |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China