

Solvay Specialty Polymers Veradel® 3600P Polyethersulfone (PESU)

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

Material Notes:

Veradel® PESU was formerly marketed as Gafonea, PESU. Veradel® 3000P, 3100P, 3200P, 3400P and 3600P are polyethersulfone (PESU) powders for dissolving or dispersing into solutions. They can also be ground to smaller particle size or blended with other solid particles. The grades differ by their molecular weights, with 3000P the highest and 3600P the lowest. There is a direct correlation between molecular weight and solution viscosity. Features: Acid Resistant; Flame Retardant; Food Contact Acceptable; Good Adhesion; Good Chemical Resistance; Good Creep Resistance; Good Dimensional Stability; Good Thermal Stability; Good Toughness; High Flow; High Heat Resistance; High Tensile Strength; Hydrolysis Resistant; Low Molecular Weight; Medium Rigidity Uses: Adhesives; Binder; Coating Applications; Compounding Additional Properties: Residual Solvent - Internal Method 0.50 % Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Veradel-3600P-Polyethersulfone-PESU.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ASTM D792
Water Absorption	0.60 % @Time 86400 sec	0.60 % @Time 24.0 hour	ISO 62
Viscosity	275 cP	275 cP	Solution Viscosity; ASTM D455

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	49.0 µm/m-°C	27.2 µin/in-°F	
Glass Transition Temp, Tg	220 °C	428 °F	ASTM E1356

Compliance Properties	Metric	English	Comments
NSF	Yes	Yes	NSF 51

Descriptive Properties	Value	Comments
Agency Ratings	NSF 51	
Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	Latin America	
	North America	

Descriptive Properties	Value	Comments
Form	parent - Slight Yellow Granules; Powder	
Processing Technique	Coating; Solution Processing; Spraying	
RoHS Compliance	RoHS Compliant	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China