

Solvay Specialty Polymers Veradel[®] AG-330 Polyethersulfone (PESU), 30% Glass Fiber

Category : Polymer , Thermoplastic , Polyethersulfone (PES) , Polyethersulfone (PES), 30%Glass Fiber Filled

Material Notes:

Veradel[®] AG-330 is a 30% glass fiber reinforced grade of polyethersulfone (PESU). Adding glass fiber to polyethersulfone substantially increases the rigidity, tensile strength, creep resistance, dimensional stability and chemical resistance of the material, while maintaining most of its other basic characteristics. The combination of structural properties and cost effectiveness make this resin an attractive alternative to metals in many engineering applications. Features: Acid Resistant; Flame Retardant; Food Contact Acceptable; Good Adhesion; Good Chemical Resistance; Good Creep Resistance; Good Dimensional Stability; Good Strength; Good Thermal Stability; Good Toughness; High Heat Resistance; High Rigidity; High Tensile Strength; Hydrolysis Resistant; Medium Flow; Medium Molecular Weight Uses: Appliance Components; Appliances; Automotive Electronics; Batteries; Business Equipment; Electrical Parts; Electrical/Electronic Applications; Food Service Applications; Industrial Applications; Metal Replacement; Microwave Cookware; Plumbing Parts; Valves/Valve Parts Information provided by Solvay Specialty Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Solvay-Specialty-Polymers-Veradel-AG-330-Polyethersulfone-PESU-30-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.58 g/cc	0.0571 lb/in ³	ASTM D792
Filler Content	30 %	30 %	Glass Fiber
Water Absorption	0.40 % @Time 86400 sec	0.40 % @Time 24.0 hour	ISO 62
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	
Melt Flow	4.5 g/10 min @Load 2.16 kg, Temperature 343 °C	4.5 g/10 min @Load 4.76 lb, Temperature 649 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	ASTM D638
Elongation at Break	1.9 %	1.9 %	ASTM D638
Tensile Modulus	8.62 GPa	1250 ksi	ASTM D638
Flexural Strength	179 MPa	26000 psi	ASTM D790
Flexural Modulus	8.62 GPa	1250 ksi	ASTM D790
Izod Impact, Notched	0.750 J/cm	1.41 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	31.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	17.2 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	216 $\text{Å}^\circ\text{C}$	421 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Flammability, UL94	V-0 @Thickness 0.787 mm	V-0 @Thickness 0.0310 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+16$ ohm-cm	$\geq 1.00\text{e}+16$ ohm-cm	ASTM D257
Dielectric Constant	4.11 @Frequency 60.0 Hz	4.11 @Frequency 60.0 Hz	ASTM D150
	4.13 @Frequency 1000 Hz	4.13 @Frequency 1000 Hz	ASTM D150
	4.17 @Frequency 1.00e+6 Hz	4.17 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	17.0 kV/mm	432 kV/in	ASTM D149
Dissipation Factor	0.0018 @Frequency 1000 Hz	0.0018 @Frequency 1000 Hz	ASTM D150
	0.0019 @Frequency 60.0 Hz	0.0019 @Frequency 60.0 Hz	ASTM D150
	0.0094 @Frequency 1.00e+6 Hz	0.0094 @Frequency 1.00e+6 Hz	ASTM D150

Compliance Properties	Metric	English	Comments
NSF	Yes	Yes	NSF 51

Processing Properties	Metric	English	Comments
Melt Temperature	343 - 399 $\text{Å}^\circ\text{C}$	649 - 750 $\text{Å}^\circ\text{F}$	
Mold Temperature	149 - 163 $\text{Å}^\circ\text{C}$	300 - 325 $\text{Å}^\circ\text{F}$	
Drying Temperature	149 - 177 $\text{Å}^\circ\text{C}$ @Time 9000 - 14400	300 - 351 $\text{Å}^\circ\text{F}$	

Processing Properties	sec Metric	@Time 2.50 - 4.00 hour English	Comments
Descriptive Properties		Value	Comments
Agency Ratings		NSF 51	
Availability		Africa & Middle East	
		Asia Pacific	
		Europe	
		Latin America	
		North America	
Color		Black; Colors; Natural	
Form		Pellets	
Injection Rate		Fast	
Processing Technique		Injection Molding	
RoHS Compliance		RoHS Compliant	
Screw Compression Ratio		2.0:1.0	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China