

## Spartech EP6120 Filled and Reinforced Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler

### Material Notes:

Filled copolymers offer a higher level of impact performance than homopolymer materials, and higher stiffness than unfilled copolymers. Copolymer based materials retain much of their impact strength at low temperatures. Typical applications include thermoformed frozen food containers, extruded and blow molded automotive and construction materials, and blow molded recreational equipment. Information provided by Spartech

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Spartech-EP6120-Filled-and-Reinforced-Copolymer.php](http://www.lookpolymers.com/polymer_Spartech-EP6120-Filled-and-Reinforced-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
	@Temperature 22.8 °C	@Temperature 73.0 °F	
Filler Content	20 %	20 %	
Linear Mold Shrinkage	0.014 cm/cm	0.014 in/in	0.125inch wall

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	29.0 MPa	4200 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Elongation at Yield	6.0 %	6.0 %	ASTM D638
Flexural Modulus	1.59 GPa	230 ksi	secant; ASTM D790
	2.14 GPa	310 ksi	tangent; ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	ASTM D256
	@Temperature 22.8 °C	@Temperature 73.0 °F	
Gardner Impact	2.71 J	2.00 ft-lb	ASTM D5420
	@Temperature -5.56 °C	@Temperature 22.0 °F	
	13.6 J	10.0 ft-lb	ASTM D5420
	@Temperature 22.8 °C	@Temperature 73.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	220 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	57.2 °C	135 °F	ASTM D648

Optical Properties	Metric	English	Comments
Gloss	45 %	45 %	60°; ASTM D523

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China