

Special Metals DURANICKEL® 301 (UNS N03301) Hot-Finished and Aged Rod and Bar

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

Tensile strength (ultimate and yield), hardness, and elongation values reported here are typical for Hot-Finished and Aged Rod and Bar specifically. Other property values are typical of aged DURANICKEL® alloy 301 or the alloy in general. Data provided by the manufacturer, Special Metals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Special-Metals-DURANICKEL-301-UNS-N03301-Hot-Finished-and-Aged-Rod-and-Bar.php

Physical Properties	Metric	English	Comments
Density	8.19 g/cc	0.296 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	300 - 375	300 - 375	3000 kg
Hardness, Rockwell C	32 - 42	32 - 42	
Tensile Strength, Ultimate	1100 - 1380 MPa	160000 - 200000 psi	
Tensile Strength, Yield	793 - 1030 MPa @Strain 0.200 %	115000 - 150000 psi @Strain 0.200 %	
Elongation at Break	15 - 30 %	15 - 30 %	
Modulus of Elasticity	207 GPa	30000 ksi	Tension
Poissons Ratio	0.31	0.31	
Fatigue Strength	350 MPa @# of Cycles 1.00e+8	50800 psi @# of Cycles 1.00e+8	rotating beam (Aging - 595°C/16 h F.C. to 540°C, AC)
Shear Modulus	76.0 GPa	11000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	13.0 µm/m-°C	7.22 µin/in-°F	Mean
	@Temperature 21.0 - 100 °C	@Temperature 69.8 - 212 °F	
	14.0 µm/m-°C	7.78 µin/in-°F	Mean
	@Temperature 21.0 - 300 °C	@Temperature 69.8 - 572 °F	
	14.7 µm/m-°C	8.17 µin/in-°F	

Thermal Properties	Metric	English	Mean Comments
	@Temperature 21.0 - 500 Â°C	@Temperature 69.8 - 932 Â°F	
	16.6 Âµm/m-Â°C	9.22 Âµin/in-Â°F	Mean
	@Temperature 21.0 - 900 Â°C	@Temperature 69.8 - 1650 Â°F	
Thermal Conductivity	23.8 W/m-K	165 BTU-in/hr-ftÂ²-Â°F	
Melting Point	1400 - 1440 Â°C	2550 - 2620 Â°F	
Solidus	1400 Â°C	2550 Â°F	
Liquidus	1440 Â°C	2620 Â°F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	4.0 - 4.75 %	4.0 - 4.75 %	
Carbon, C	<= 0.30 %	<= 0.30 %	
Copper, Cu	<= 0.25 %	<= 0.25 %	
Iron, Fe	<= 0.60 %	<= 0.60 %	
Manganese, Mn	<= 0.50 %	<= 0.50 %	
Nickel, Ni	>= 93 %	>= 93 %	Including Cobalt
Silicon, Si	<= 1.0 %	<= 1.0 %	
Sulfur, S	<= 0.010 %	<= 0.010 %	
Titanium, Ti	0.25 - 1.0 %	0.25 - 1.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000424 ohm-cm	0.0000424 ohm-cm	
Curie Temperature	<= 95.0 Â°C	<= 203 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China