

## Styrolution Styrolux<sup>®</sup> GH 62 SBC

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene-Butadiene Copolymer, SBC

### Material Notes:

Description: Styrolux<sup>®</sup> GH 62 is a high flow thermoplastic styrene-butadiene block copolymer with excellent mold release properties. It has crystal clarity, good toughness, good stiffness and warpage resistance for general injection molding applications. Styroclear GH 62 may be suitable for conventional thermoplastics processing technologies such as injection molding. Information provided by STYROLUTION, which is a joint venture between BASF and INEOS

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Styrolution-Styrolux-GH-62-SBC.php](http://www.lookpolymers.com/polymer_Styrolution-Styrolux-GH-62-SBC.php)

Physical Properties	Metric	English	Comments
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	69	69	ASTM D2240
Tensile Strength, Yield	28.0 MPa	4060 psi	2in/min; ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Tensile Modulus	1.73 GPa	251 ksi	2in/min; ASTM D882
Flexural Strength	31.0 MPa	4500 psi	ASTM D790
Flexural Modulus	1.48 GPa	215 ksi	ASTM D790
Dart Drop, Total Energy	5.00 J	3.69 ft-lb	Total energy; ASTM D3763

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	66.0 Å°C	151 Å°F	ASTM D648
Vicat Softening Point	91.0 Å°C @Load 1.02 kg, Temperature 120 Å°C	196 Å°F @Load 2.25 lb, Temperature 248 Å°F	ASTM D1525

Optical Properties	Metric	English	Comments
Transmission, Visible	92 %	92 %	ASTM D1003

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 250 Å°C	356 - 482 Å°F	Injection
Mold Temperature	30.0 - 50.0 Å°C	86.0 - 122 Å°F	

Processing Properties	Metric	English	Comments
Descriptive Properties		Value	Comments
Commercial Status		North America	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China