

Styron Buna® SB 1502 Schkopau Cold Polymerized Emulsion Styrene Butadiene Rubber (E-SBR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

Material Notes:

Composition: Buna® SB 1502 Schkopau is manufactured by cold polymerization using mixed rosin acid /fatty acid soaps. A non-discoloring stabilizer is added during the production process. Application: Buna® SB 1502 Schkopau is a general purpose rubber. It can be processed in all sectors of the tyre and rubber industry. Buna® SB 1502 Schkopau is mainly used for the production of light-colored rubber articles which can also be applied in the food industry (Styron may be consulted regarding applicable regulations). Test Formulation (ASTM D 3189 based on IRB7 black): Polymer - 100.0 parts by mass IRB7 industry reference oil furnace carbon black - 50.0 parts by mass Zinc oxide - 3.0 parts by mass Sulphur - 1.75 parts by mass Stearic acid - 1.0 parts by mass N-tert-butyl-2-benzothiazole sulphenamide (TBBS) - 1.0 parts by mass Information provided by Styron

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styron-Buna-SB-1502-Schkopau-Cold-Polymerized-Emulsion-Styrene-Butadiene-Rubber-E-SBR.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	
Volatiles	0.30 % @Treatment Temp. 105 °C, Time 3600 sec	0.30 % @Treatment Temp. 221 °F, Time 1.00 hour	5 g in hot air oven; ASTM D5668
Mooney Viscosity	50 @Temperature 100 °C	50 @Temperature 212 °F	[MU] ML 1+4; ASTM D1646
Ash	0.050 %	0.050 %	ASTM D5667

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	28.4 MPa @Treatment Temp. 145 °C, Time 2100 sec	4120 psi @Treatment Temp. 293 °F, Time 0.583 hour	Cure; ASTM D412
Elongation at Break	490 %	490 %	ASTM D412
300% Modulus	0.0155 GPa	2.25 ksi	ASTM D412

Chemical Properties	Metric	English	Comments
Styrene Content	23.5 %	23.5 %	Bound; ASTM D5775

Descriptive Properties	Value	Comments
------------------------	-------	----------

Composition Descriptive Properties	0.058 Value	Organic Acid, ASTM D5774 Comments
Rheometer	15.8 min	t _c (90), ASTM D5289
	2.6 dNm	ML, ASTM D5289
	21.9 dNm	MH, ASTM D5289
	5.6 min	t _s ² , test temperature 160Å°C; ASTM D5289
	9.2 min	t _c (50), ASTM D5289

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China