

Styron Magnum[®] 358HP ABS, High Heat

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Heat Resistant, Molded

Material Notes:

MAGNUM[®] ABS resins are thermoplastic materials which provide an excellent balance of processability, impact resistance and heat resistance as imparted by the various polymer compositions. MAGNUM ABS resin are available in a wide range of melt flow rates, impact strength and heat resistance for both high and low gloss applications manufactured by injection molding, sheet or profile extrusion and thermoforming. The Automotive grades of MAGNUM ABS resins offer a wide range of gloss, viscosity, impact strength and heat properties for use in numerous automotive applications. Melt flow rates from 1 to 12 g/10 min, impact strengths from 130 to 590 J/m and heat distortion temperatures from 77.C to 90.C are available. Available primarily as natural plus concentrates, MAGNUM ABS resins are used in a wide variety of automotive applications including structural instrument panels, consoles, pillars and exterior trim parts requiring painting and plating. MAGNUM 358 HP ABS resin is a high heat, low gloss resin having unannealed DTUL values of 90.C at 1.8 MPa loading. MAGNUM 358 HP ABS resin is often used in switch plates, demister grilles and door rollovers, and visor covers. Data provided by Dow Chemical. This product line was spun off from Dow Chemical to Styron in 2010.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styron-Magnum-358HP-ABS-High-Heat.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM Data
Linear Mold Shrinkage	0.0055 cm/cm	0.0055 in/in	
Melt Flow	2.5 g/10 min @Load 3.80 kg, Temperature 230 °C	2.5 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM Data

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	40.0 MPa	5800 psi	ISO Data
Tensile Strength, Yield	47.6 MPa	6900 psi	ASTM Data
Elongation at Break	15 %	15 %	ASTM Data
Tensile Modulus	2.34 GPa	339 ksi	ASTM Data
Izod Impact, Notched	2.19 J/cm	4.10 ft-lb/in	ASTM Data
Charpy Impact Unnotched	6.00 J/cm ²	28.6 ft-lb/in ²	ISO Data, Low Temp
	NB	NB	ISO Data
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO Data, Low Temp
	1.80 J/cm ²	8.57 ft-lb/in ²	ISO Data
	21.0 J	15.5 ft-lb	

Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	Comments
	42.0 J	31.0 ft-lb	Instrumented Dart Total Energy
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	77.4 $\mu\text{m}/\text{m}\cdot\text{°C}$ @Temperature 20.0 °C	43.0 $\mu\text{in}/\text{in}\cdot\text{°F}$ @Temperature 68.0 °F	ASTM data
Deflection Temperature at 0.46 MPa (66 psi)	105 °C	221 °F	Unannealed; ASTM Data
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	Unannealed; ASTM Data
Vicat Softening Point	117 °C	243 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China