

Styron Magnum[®] 9555 ABS, High Impact

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Heat Resistant, Molded

Material Notes:

MAGNUM[®] ABS resins are thermoplastic materials which provide an excellent balance of processability, impact resistance and heat resistance as imparted by the various polymer compositions. MAGNUM ABS resin are available in a wide range of melt flow rates, impact strength and heat resistance for both high and low gloss applications manufactured by injection molding, sheet or profile extrusion and thermoforming. The MAGNUM 9000 series of high gloss ABS resins are designed to offer a wide range of impact strengths and melt flow rates to meet the needs of the durables injection molding markets. The 9000 series products offer typical Izod impact strength values from 210 to 400 J/m and melt flow rates ranging from 2.5 to 7.0 g/10min. The gloss values are typically greater than 95% on the 60. Gardner scale for the highest gloss resins and greater than 90% for those products having a broader range of gloss. MAGNUM 9555 ABS resin offers a broader range of gloss while maintaining high impact strength with a medium melt flow rate. Data provided by Dow Chemical. This product line was spun off from Dow Chemical to Styron in 2010.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styron-Magnum-9555-ABS-High-Impact.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM Data
Linear Mold Shrinkage	0.0055 cm/cm	0.0055 in/in	
Melt Flow	5.0 g/10 min	5.0 g/10 min	ASTM Data
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	107	107	
Tensile Strength, Ultimate	31.0 MPa	4500 psi	ASTM Data
Tensile Strength, Yield	44.8 MPa	6500 psi	ASTM Data
Elongation at Break	40 %	40 %	ASTM Data
Elongation at Yield	2.3 %	2.3 %	ISO Data
Tensile Modulus	2.24 GPa	325 ksi	ASTM Data
Izod Impact, Notched	3.20 J/cm	5.99 ft-lb/in	ASTM Data
Charpy Impact Unnotched	NB	NB	ISO Data
	NB	NB	ISO Data, Low Temp
Charpy Impact, Notched	0.900 J/cm ²	4.28 ft-lb/in ²	ISO Data, Low Temp

Mechanical Properties	2.90 J/cm ² Metric	13.8 ft-lb/in ² English	ISO Data Comments
Impact Test	55.0 J @Temperature 23.0 Â°C	40.6 ft-lb @Temperature 73.4 Â°F	Instrumented Dart Total Energy

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	91.0 Âµm/m-Â°C @Temperature 20.0 Â°C	50.6 Âµin/in-Â°F @Temperature 68.0 Â°F	ISO data
Deflection Temperature at 0.46 MPa (66 psi)	92.0 Â°C	198 Â°F	Unannealed; ASTM Data
Deflection Temperature at 1.8 MPa (264 psi)	77.0 Â°C	171 Â°F	Unannealed; 103Â°C (217Â°F) annealed; ASTM Data
Vicat Softening Point	106 Â°C	223 Â°F	
Flammability, UL94	HB @Thickness 1.47 mm	HB @Thickness 0.0579 in	

Optical Properties	Metric	English	Comments
Gloss	90 %	90 %	Gardner Gloss, 60Â°

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China