

Sumitomo Bakelite North America 2-530 Short-Glass Reinforced Diallyl Phthalate

Category : Polymer , Thermoset , Diallyl Phthalate (DAP) , Diallyl Phthalate (DAP) Molding Compound, Short Glass Fiber Filled , Filled/Reinforced Thermoset

Material Notes:

Isophthalate DAP Resin Isomer. Used for critical, high-performance military and commercial electrical components where long-term reliability is demanded. Information provided by Sumitomo Bakelite North America, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sumitomo-Bakelite-North-America-2-530-Short-Glass-Reinforced-Diallyl-Phthalate.php

Physical Properties	Metric	English	Comments
Density	1.73 g/cc	0.0625 lb/in ³	ASTM D792
Apparent Bulk Density	0.490 g/cc	0.0177 lb/in ³	
Water Absorption	0.35 %	0.35 %	48 hours, 50°C. ASTM D570
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	Compression Molding. ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	69.0 MPa	10000 psi	ASTM D638
Flexural Yield Strength	131 MPa	19000 psi	ASTM D790
Flexural Modulus	13.8 GPa	2000 ksi	ASTM D790
Compressive Yield Strength	152 MPa	22000 psi	ASTM D695
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	ASTM D256A

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	15.0 Åµm/m-Å°C @Temperature 20.0 Å°C	8.33 Åµin/in-Å°F @Temperature 68.0 Å°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	288 Å°C	550 Å°F	ASTM D648A
Oxygen Index	25 %	25 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.6 @Frequency 1e+6 Hz	3.6 @Frequency 1e+6 Hz	Wet

Electrical Properties	^{3.8} Metric	^{3.8} English	Comments
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dielectric Strength	15.0 kV/mm	381 kV/in	Wet, step-by-step. ASTM D149
	16.0 kV/mm	406 kV/in	Wet, short term. ASTM D149
Dissipation Factor	0.010	0.010	Wet; ASTM D150
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.019	0.019	Wet; ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	135 sec	135 sec	ASTM D495

Processing Properties	Metric	English	Comments
Processing Temperature	160 - 180 Â°C	320 - 356 Â°F	Mold temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China