

## Sumitomo Chemical ESPOLEX® 3785 Thermoplastic Elastomer

Category: Polymer, Thermoplastic, Elastomer, TPE

## **Material Notes:**

ESPOLEX® TPE Series is a group of thermoplastic elastomers produced by Sumitomo Chemical Company. Among its material advantages, ESPOLEX® TPE Series is distinguished by offering many low-density grades that can provide substantial weight and cost savings over higher-density thermoplastic elastomers. In this regard, SUMITOMO CHEMICAL introduces specific gravity as a significant factor in reducing unit cost and weight. Products molded from ESPOLEX® TPE Series exhibit rubber-like properties that range from a soft elastic to a semi-hard rubber material. Like all thermoplastic elastomers, ESPOLEX® TPE Series offers substantial savings over thermoset rubber in manufacturing since it is processed using standard thermoplastic processing equipment and techniques, and it does not require the vulcanization required by conventional rubbers.Information provided by Sumitomo Chemical

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Sumitomo-Chemical-ESPOLEX-3785-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Density	0.880 g/cc	0.0318 lb/in³	ASTM D792
Melt Flow	50 g/10 min	50 g/10 min	ASTM D1238
	@Load 10.00 kg	@Load 22.05 lb	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	10 Sec Delay; ASTM D2240
	72	72	0 Sec Delay; ASTM D2240
Tensile Strength at Break	5.50 MPa	798 psi	ASTM D412
Elongation at Break	530 %	530 %	ASTM D412
Compression Set	29 %	29 %	ASTM D395
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	40 %	40 %	ASTM D395
	@Temperature 70.0 °C	@Temperature 158 °F	

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	200 - 240 °C	392 - 464 °F	
Mold Temperature	30.0 - 50.0 °C	86.0 - 122 °F	

## Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China