

Sumitomo Chemical ESPOLEX® 903 Thermoplastic Elastomer

Category: Polymer, Thermoplastic, Elastomer, TPE

Material Notes:

ESPOLEX® TPE Series is a group of thermoplastic elastomers produced by Sumitomo Chemical Company. Among its material advantages, ESPOLEX® TPE Series is distinguished by offering many low-density grades that can provide substantial weight and cost savings over higher-density thermoplastic elastomers. In this regard, SUMITOMO CHEMICAL introduces specific gravity as a significant factor in reducing unit cost and weight. Products molded from ESPOLEX® TPE Series exhibit rubber-like properties that range from a soft elastic to a semi-hard rubber material. Like all thermoplastic elastomers, ESPOLEX® TPE Series offers substantial savings over thermoset rubber in manufacturing since it is processed using standard thermoplastic processing equipment and techniques, and it does not require the vulcanization required by conventional rubbers.Information provided by Sumitomo Chemical

Order this product through the following link:

http://www.lookpolymers.com/polymer_Sumitomo-Chemical-ESPOLEX-903-Thermoplastic-Elastomer.php

| Physical Properties | Metric | English | Comments |
|---------------------|---------------|---------------|------------|
| Density | 0.905 g/cc | 0.0327 lb/in³ | ASTM D792 |
| Melt Flow | 6.4 g/10 min | 6.4 g/10 min | ASTM D1238 |
| | @Load 2.20 kg | @Load 4.86 lb | |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|-----------|----------|--------------------------|
| Hardness, Shore D | 52 | 52 | 10 Sec Delay; ASTM D2240 |
| | 62 | 62 | 0 Sec Delay; ASTM D2240 |
| Tensile Strength at Break | 15.0 MPa | 2180 psi | ASTM D412 |
| Elongation at Break | 520 % | 520 % | ASTM D412 |
| Flexural Modulus | 0.550 GPa | 79.8 ksi | ASTM D790 |

| Processing Properties | Metric | English | Comments |
|---------------------------|----------------|---------------|----------|
| Middle Barrel Temperature | 200 - 245 °C | 392 - 473 °F | |
| Mold Temperature | 30.0 - 50.0 °C | 86.0 - 122 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058



Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China