

Supreme Petrochem SH 2157 High Impact Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Characteristics Excellent ESCR properties Good formability Processing Extrusion Applications Refrigerator door and cabinet liners Dairy containers Ice cream cups, plates and bowls Material Status: Commercial : Active Agency Ratings: FDA 21 CFR 177.1640, UL file E185934 Information provided by Supreme Petrochem LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Supreme-Petrochem-SH-2157-High-Impact-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.03 g/cc	1.03 g/cc	ASTM D792
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 Â°C	@Load 11.0 lb, Temperature 392 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	19.6 MPa	2840 psi	50 mm/min; ASTM D638
Elongation at Break	50 %	50 %	50 mm/min; ASTM D638
Flexural Strength	34.3 MPa	4970 psi	ASTM D790
	@Thickness 3.20 mm	@Thickness 0.126 in	
Flexural Modulus	1.47 GPa	213 ksi	ASTM D790
	@Thickness 3.20 mm	@Thickness 0.126 in	
Izod Impact, Notched	1.10 J/cm	2.06 ft-lb/in	ASTM D256
	@Thickness 3.20 mm	@Thickness 0.126 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	76.0 Â°C	169 Â°F	ASTM D648
Vicat Softening Point	98.0 Â°C	208 Â°F	1kg / 120Â°C; ASTM D1525
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 260 Â°C	356 - 500 Â°F	

Mold Temperature Processing Properties	40.0 - 60.0 A°C Metric	104 - 140 A°F English	Comments
---	---------------------------	--------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China