

Supreme Petrochem SP 564 Flame Retardant Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Flame Retardant

Material Notes:

Characteristics Very good flow properties Free of DBDPO, PBDE & TBBA, complies with ROHS directive of EU Processing

MoldingApplications Large size T.V. Cabinets VCR cabinets Electrical boxes, electrical appliance partsMaterial Status: Commercial :

ActiveAgency Ratings: Information provided by Supreme Petrochem LTD

Order this product through the following link:

http://www.lookpolymers.com/polymer_Supreme-Petrochem-SP-564-Flame-Retardant-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Melt Flow	20 g/10 min @Load 5.00 kg, Temperature 200 Â°C	20 g/10 min @Load 11.0 lb, Temperature 392 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	24.5 MPa	3550 psi	50 mm/min; ASTM D638
Elongation at Break	35 %	35 %	50 mm/min; ASTM D638
Flexural Strength	37.3 MPa @Thickness 3.20 mm	5410 psi @Thickness 0.126 in	ASTM D790
Flexural Modulus	1.81 GPa @Thickness 3.20 mm	263 ksi @Thickness 0.126 in	ASTM D790
Izod Impact, Notched	1.10 J/cm @Thickness 3.20 mm	2.06 ft-lb/in @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
Hot Ball Pressure Test	75.0 Â°C	167 Â°F	IEC335-1
Deflection Temperature at 1.8 MPa (264 psi)	78.0 Â°C	172 Â°F	ASTM D648
Vicat Softening Point	97.0 Â°C	207 Â°F	1kg / 120Â°C; ASTM D1525
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
Glow Wire Test	960 Â°C	1760 Â°F	IEC 695-2-1

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00 \times 10^{16}$ ohm-cm	$\geq 1.00 \times 10^{16}$ ohm-cm	IEC 93
Surface Resistance	$\geq 1.00 \times 10^{14}$ ohm	$\geq 1.00 \times 10^{14}$ ohm	IEC 93
Dielectric Constant	2.6 @Frequency 1e+6 Hz	2.6 @Frequency 1e+6 Hz	IEC 250
Dissipation Factor	0.00040 @Frequency 1e+6 Hz	0.00040 @Frequency 1e+6 Hz	IEC 250

Processing Properties	Metric	English	Comments
Melt Temperature	≤ 250 Â°C	≤ 482 Â°F	
Mold Temperature	40.0 - 60.0 Â°C	104 - 140 Â°F	
Drying Temperature	60.0 - 80.0 Â°C	140 - 176 Â°F	Pre drying temp.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China