

## TIMCAL TIMREX® KS75 Primary Synthetic Graphite

Category : Carbon , Graphite , Other Engineering Material , Additive/Filler for Polymer

### Material Notes:

TIMREX Primary Synthetic Graphite is produced in a unique highly controlled graphitization process which assures narrow specifications and unequalled consistent quality due to: monitoring of all production and processing stages, strict final inspection, and clearly defined development processes. TIMREX Primary Synthetic Graphite shows unique properties thanks to the combination of a consistent purity, perfect crystalline structure and well defined texture. Tribological and mechanical properties: Medium toughness Good lubrication properties Advantages and applications: Low friction coefficient Low wear of the counterpart Good transfer-film formation High electrical conductivity Suitable for pitch-bonded and resin-bonded brushes Fe-self lubricating engineering parts Fe-friction parts Copper/bronze bearings Copper friction parts copper clutch facings Information provided by TIMCAL

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TIMCAL-TIMREX-KS75-Primary-Synthetic-Graphite.php](http://www.lookpolymers.com/polymer_TIMCAL-TIMREX-KS75-Primary-Synthetic-Graphite.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.240 g/cc	0.00867 lb/in <sup>3</sup>	Scott
Particle Size	5.0 µm	5.0 µm	Springback 11.5%, pressure 0.477 t/cc
	20 µm	20 µm	Springback 13%, pressure 0.477 t/cc
	23.1 µm	23.1 µm	d50
	55.8 µm	55.8 µm	d90
	48 - 65 µm	48 - 65 µm	d90, Guaranteed
	75 µm	75 µm	Springback 17%, pressure 0.477 t/cc
	550 µm	550 µm	at a density of 2.16 g/cc
Deformation	1000 µm	1000 µm	at a density of 2.12 g/cc
	1.4 %	1.4 %	plastic
	1.4 %	1.4 %	elastic
Ash	2.8 %	2.8 %	plastic + elastic
	0.070 %	0.070 %	Typical
	<= 0.10 %	<= 0.10 %	Guaranteed

Mechanical Properties	Metric	English	Comments
Coefficient of Friction	0.30	0.30	Friction coefficient of sintered Cu-C - brake pads with 10% TIMREX® KS Graphite as a function of the particle size, Sinterdensity: 55% of the
	@Temperature 850 °C,	@Temperature 1560 °F,	

Mechanical Properties	Time 10800 sec Metric	Time 3.00 hour English	theoret. density Comments
-----------------------	--------------------------	---------------------------	------------------------------

Thermal Properties	Metric	English	Comments
Thermal Conductivity	140 W/m-K	972 BTU-in/hr-ft <sup>2</sup> -°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.55 ohm-cm	1.55 ohm-cm	particle size 80 um, pressure 2.5 t/cc
	1.60 ohm-cm	1.60 ohm-cm	particle size 42 um, pressure 2.5 t/cc
	1.80 ohm-cm	1.80 ohm-cm	particle size 15 um, pressure 2.5 t/cc
	2.25 ohm-cm	2.25 ohm-cm	particle size 10 um, pressure 2.5 t/cc

Processing Properties	Metric	English	Comments
Moisture Content	0.10 %	0.10 %	Typical
	<= 0.50 %	<= 0.50 %	Guaranteed

Descriptive Properties	Value	Comments
Crystallite Height	>100 nm	
DBP absorption	98 g/100g	(Dibutylphthalate)

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China