

## TIMCAL TIMREX® T15-75 Primary Synthetic Graphite

Category : Carbon , Graphite , Other Engineering Material , Additive/Filler for Polymer

### Material Notes:

TIMREX Primary Synthetic Graphite is produced in a unique highly controlled graphitization process which assures narrow specifications and unequalled consistent quality due to: monitoring of all production and processing stages, strict final inspection, and clearly defined development processes. TIMREX Primary Synthetic Graphite shows unique properties thanks to the combination of a consistent purity, perfect crystalline structure and well defined texture. Tribological and mechanical properties: High toughness Good lubrication properties Advantages and applications: Low friction coefficient Low wear of the counterpart and low self-wear Good transfer-film formation Medium electrical conductivity Medium density of brushes and parts Suitable for pitch-bonded and resin-bonded brushes Information provided by TIMCAL

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TIMCAL-TIMREX-T15-75-Primary-Synthetic-Graphite.php](http://www.lookpolymers.com/polymer_TIMCAL-TIMREX-T15-75-Primary-Synthetic-Graphite.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.330 g/cc	0.0119 lb/in <sup>3</sup>	Scott
Particle Size	43 µm	43 µm	springback 20.5%, pressure at 0.477 t/cc
	45 - 76 µm	45 - 76 µm	d90, Guaranteed
	61 µm	61 µm	d90, Typical
	70 µm	70 µm	at a density of 2.20 g/cc
	75 µm	75 µm	springback 23%, pressure at 0.477 t/cc
	145 µm	145 µm	springback 24%, pressure at 0.477 t/cc
	625 µm	625 µm	at a density of 2.10 g/cc
Deformation	1500 µm	1500 µm	at a density of 2.02 g/cc
	1.1 %	1.1 %	elastic
	2.6 %	2.6 %	plastic
Ash	3.7 %	3.7 %	plastic + elastic
	0.030 %	0.030 %	Typical
	<= 0.10 %	<= 0.10 %	Guaranteed

Thermal Properties	Metric	English	Comments
Thermal Conductivity	130 W/m-K	902 BTU-in/hr-ft <sup>2</sup> -°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	2.25 ohm-cm	2.25 ohm-cm	particle size 40 um, pressure at 2.5 t/cc
	2.50 ohm-cm	2.50 ohm-cm	particle size 70 um, pressure at 2.5 t/cc

Processing Properties	Metric	English	Comments
Moisture Content	0.020 %	0.020 %	Typical
	<= 0.50 %	<= 0.50 %	Guaranteed

Descriptive Properties	Value	Comments
Crystallite Height, Lc	>100 nm	
DBP absorption	70 g/100g	(Dibutylphthalate)

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China